15

30

35

\What is claimed is:

1. A polyolefin, which contains about 80 to about 150 branches per 1000 methylene groups, and which contains for every 100 branches that are methyl / about 30 to about 90 ethyl branches, about 4 to about 20 propyl branches, about 15 to about 50 butyl branches, about 3 to about 15 amyl branches, and about 30 to about 140 hexyl or longer branches.

- 2. The polyolefin as recited in claim 1 which contains about 100 to about 130 branches per 1000 methylene groups, and which contains for every 100 branches that are methyl, about 50 to about 75 ethyl branches, about 5 to about 15 propyl branches, about 24 to about 40 butyl branches, about 5 to about 10 amyl branches, and about 65 to about 120 hexyl or longer branches.
- 3. The polyolefin as recited in claim 1 which is an ethylene homopolymer.
- 4. A polyolefin which/contains about 20 to about 150 branches per 1000 methy ene groups and which contains for every 100 branches that are methyl, about 20 4 to about 20 ethyl branches, about 1 to about 12 propyl branches, about 1 to about 12 butyl branches, about 1 to about 10 amyl branches, and 0 to about 20 hexyl or longer branches. 25
 - 5. The polyofefin as recited in claim 4 which contains about 4 to about 100 branches per 1000 methylene groups, and which contains for every 100 branches that are methyl, about 6 to about 15 ethyl branches, about 2 to about 10 propyl branches, about 2 to about 10 butyl branches, about 2 to about 8 amyl branches, and about 2 to about 15 hexyl or longer branches.
 - 6. The polyolefin as recited in claim 4 which is an ethy/ene homopolymer.
 - 7/ A polymer, consisting essentially of units derived from the monomers ethylene and a compound of the formula $CH_2=CH(CH_2)_mCO_2R^1$, wherein R^1 is hydrogen,

10

15

20

25

hydrocarbyl or substituted hydrocarbyl, and m is 0 or an integer from 1 to 16, and which contains about 0.01 to about 40 mole percent of repeat units derived from said compound, and provided that said repeat units derived from said compound are in branches of the formula $-CH(CH_2)_nCO_2R^1$, in about 30 to about 70 mole percent of said branches n is 5 or more, in about 0 to about 20 mole percent n is 4, in about 3 to 60 mole percent n is 1, 2 and 3, and in about 1 to about 60 mole percent n is 0.

8. The polymer as recited in claim 7 wherein m is

0.

9. The polymer as recited in claim 7 wherein R^1 is hydrocarbyl or substituted hydrocarbyl.

10. The polymer as recited in claim 7 wherein R¹ is alkyl containing 1 to 10 carbon atoms.

11. The polymer as recited in claim 8 wherein R¹ is hydrocarbyl or substituted hydrocarbyl.

12. The polymer as recited in claim 7 wherein about 0.1 to about 20 mole percent of said units are derived from said compound.

13. A process for the polymerization of olefins, comprising, contacting a transition metal complex of a bidentate ligand selected from the group consisting of

R³ N R⁴ N R⁵ (VIII)

R²⁸ (CR³⁰₂)_n R²⁹ R⁴C=N N=CR⁴⁵ (XXX)

408

15

20

(XXIII)

$$\begin{array}{c|c}
R^{20} \\
 & H \\
 & R^{21} \\
 & N \\
 & R^{22} \\
 & N \\
 & R^{23}
\end{array}$$

(XXXII)

with an olefin wherein:

said olefin is selected from the group consisting of ethylene, an olefin of the formula $R^{17}CH=CH_2$ or $R^{17}CH=CHR^{17}$, cyclobutene, cyclopentene, norbornene, or a substituted norbornene,;

said transition metal is selected from the group consisting of Ti, Zr, Sc, V, Cr, a rare earth metal, Fe, Co, Ni or Pd;

 R^2 and R^5 are each independently hydrocarbyl or substituted hydrocarbyl provided that the carbon atom bound to the imino nitrogen atom has at least two carbon atoms bound to it;

R³ and R⁴ are each independently hydrogen, hydrocarbyl, substituted hydrocarbyl, or R³ and R⁴ taken together are hydrocarbylene or substituted hydrocarbylene to form a carbocyclic ring;

 R^{44} is hydrocarbyl or substituted hydrocarbyl, and R^{28} is hydrogen, hydrocarbyl or substituted hydrocarbyl or R^{44} and R^{28} taken together form a ring;

R45 is hydrocarbyl or substituted hydrocarbyl, and R25 is hydrogen, substituted hydrocarbyl or/ hydrocarbyl, or R45 and R29 taken together form a ring; each R30 is independently hydrogen, substituted hydrocarbyl or hydrocarbyl, or two of R30 kaken together form a ring; R^{20} and R^{23} are independently hydrocarbyl or substituted hydrocarbyl; R^{21} and R^{22} are each in independently hydrogen, hydrocarbyl or substituted hydrocarbyl; each R¹⁷ is independently/hydrocarbyl or substituted hydrocarbyl provided that any olefinic bond in said olefin is separated from any other olefinic bond or aromatic ring by a quaternary carbon atom or at least two saturated carbon atoms; R1 is hydrogen, hydrocarbyl or substituted 15 hydrocarbyl; n is 2 or 3; and provided that when said bidentate ligand is (XXX) M is not 20 Pd; when M is Pd a diene is not present; and said transition metal also has bonded to it a ligand that may be displaced by said olefin or add to said olefin; when narbornene or substituted norbornene is 25 used no other elefin is present. 14. The process as recited in claim 13 wherein said transition metal is Co, Fe, Ni or Pd. 15. The process as recited in claim 13 wherein 30 said transition metal is Ni or Pd. 16/ The process as recited in claim 13 or 15 wherein said olefin is ethylene, R17CH=CH2, or cyclopentene, wherein R17 is n-alkyl. \prime_{17} . The process as recited in claim 13 wherein 35 said olefin comprises cyclopentene. 18. The process as recited in claim 13, 14, 15, or

410

1, wherein said bidentate ligand is (VIII).

15

20

- 19. The process as recited in claim 18 wherein said olefin is ethylene.
- 20. The process as recited is in claim 18 wherein said olefin is propylene.
- 21. The process as recited in claim 18 wherein said olefin is a combination of ethylene and propylene.
- 22. The process as recited in claim 18 wherein said olefin is contained in a mixed butenes stream.
- 23. The process as recited in claim 18 wherein R² and R⁵ are each independently hydrocarbyl provided that the carbon atom bound to the imino nitrogen atom has at least two carbon atoms bound to it; R³ and R⁴ are each independently hydrogen, hydrocarbyl, or R³ and R⁴ taken together are hydrocarbylene to form a carbocyclic ring.
 - 24. The process as recited in claim 18 wherein \mathbb{R}^3 and \mathbb{R}^4 are each independently hydrogen or methyl or together are 1,8-naphthylylene, and both \mathbb{R}^2 and \mathbb{R}^5 are 2,6-diisopropylphenyl.
 - 25. The process as recited in claim 18 wherein said olefin comprises cyclopentene.
 - 26. A process for the copolymerization of an olefin and a fluorinated plefin, comprising, contacting a transition metal complex of a bidentate ligand selected from the group consisting of

(VIII)

25

30

with an olefin and a fluorinated olefin wherein:
said olefin is selected from the group
consisting of ethylene and an olefin of the formula
R¹⁷CH=CH₂ or R¹⁷CH=CHR¹⁷;

said transition metal is selected from the group consisting of Ni and Pd;

. 5

10

15

20

25

35

said fluorinated olefin is of the formula $H_2C=CH\left(CH_2\right){}_aR_fR^{42}$;

a is an integer of 2 to 20; R_f is perfluoroalkylene optionally containing one or more ether groups;

R42 is fluorine or a functional group;

 R^2 and R^5 are each independently hydrocarbyl or substituted hydrocarbyl, provided that the carbon atom bound to the imino nitrogen atom has at least two carbon atoms bound to it;

 R^3 and R^4 are each independently hydrogen, hydrocarbyl, substituted hydrocarbyl, or R^3 and R^4 taken together are hydrocarbylene or substituted hydrocarbylene to form a carbocyclic ring;

each R¹⁷ is independently saturated hydrocarbyl;

and provided that said transition metal also has bonded to it a ligand that may be displaced by said olefin or added to said of efin.

27. The process as recited in claim 26 wherein R42 is fluorine, ester or sulfonyl halide.

28. The process as recited in claim 26 wherein R_f is -(CF₂)_b-, wherein b is 2 to 20, or -(CF₂)_dOCF₂CF₂- wherein d is 2 to 20.

29. The process as recited in claim 26 or 27 wherein said olefin is ethylene or wherein said olefin is $R^{17}CH=CH_2$, wherein R^{17} is n-alkyl.

and R⁵ are each independently hydrocarbyl, provided that the carbon atom bound to the imino nitrogen atom has at least two carbon atoms bound to it; and R³ and R⁴ are each independently hydrogen, hydrocarbyl, or R³ and R⁴ taken together are hydrocarbylene to form a carbocyclic ring.

31. A copolymer of an olefin of the formula $R^{17}CH=CHR^{17}$ and a fluorinated olefin of the formula $H_2C=CH(CH_2)_aR_fR^{42}$, wherein:

412

15

20

30

each R¹⁷ is independently hydrogen or saturated hydrocarbyl;

a is an integer of 2 to 20; R_f is perfluoroalkylene optionally containing one or more ether groups; and

 R^{42} is fluorine or a functional group; provided that when both of R^{17} are hydrogen and R^{42} is fluorine, R_f is $-(CF_2)_b$ — wherein b is 2 to 20 or perfluoroalkylene containing at least one ether group.

10 32. The copolymer as recited in claim 31 wherein \mathbb{R}^{42} is fluorine, ester, sulfonic acid, or sulfonyl halide.

33. The copolymer as recited/in claim 31 wherein R_f is -(CF₂)_b-, wherein b is 2 to/20, or -(CF₂)_dOCF₂CF₂-wherein d is 2 to 20.

34. The copolymer as recited in claim 31 or 32 wherein said olefin is ethylene or wherein said olefin is $R^{17}CH=CH_2$, wherein R^{17} is n-alkyl.

35. The copolymer as recited in claim 31 wherein said fluorinated olefin is about 1 to 20 mole percent of repeat units in said copolymer.

36. An acid catalyst of the composition of claim 31, wherein R^{42} is sulfonic acid.

37. A process for the polymerization of olefins, comprising, contacting, at a temperature of about -100°C to about +200°C:

a first compound W, which is a neutral Lewis acid capable of abstracting either Q or S to form WQ or WS, provided that the anion formed is a weakly coordinating anion; or a cationic Lewis or Bronsted acid whose counterion is a weakly coordinating anion; a second compound of the formula

(XI)

15

20

25

30

35

and one or more monomers selected from the group consisting of ethylene, an olefin of the formula R¹⁷CH=CH₂ or R¹⁷CH=CHR¹⁷, cyclobutene, cyclopentene, substituted norbornene, or norbornene;

wherein:

M is Ti, Zr, Sc, V, Cr, a rare earth metal, Fe, Co, Ni or Pd in the m oxidation state;

y + z = m

R² and R⁵ are each independently hydrocarbyl or substituted hydrocarbyl, provided that the carbon atom bound to the imino nitrogen atom has at least two carbon atoms bound to it;

R³ and R⁴ are each independently hydrogen, hydrocarbyl, substituted hydrocarbyl, or R³ and R⁴ taken together are hydrocarbylene or substituted hydrocarbylene to form a carbocyclic ring;

each R¹⁷ is independently hydrocarbyl or substituted hydrocarbyl provided that any olefinic bond in said olefin is separated from any other olefinic bond or aromatic ring by a quaternary carbon atom or at least two saturated carbon atoms;

Q is alkyl, hydride, chloride, iodide, or bromide;

S is alkyl, hydride, chloride, iodide, or bromide; and

provided that;

when norbornene or substituted norbornene is present, no other monomer is present;

when M is Pd a diene is not present; and except when M is Pd, when both Q and S are each independently chloride, bromide or iodide W is capable of transferring a hydride or alkyl group to M.

38. The process as recited in claim 37 wherein said monomer is ethylene only.

39. The process as recited in claim 37 wherein said monomer is an α -olefin only.

- 40. The process as recited in claim 39 wherein said α -olefin is propylene.
- 41. The process as recited in claim 37 done in the presence of a solvent.
- 42. The process as recited in claim 41 wherein R^3 and R^4 are each independently hydrogen or methyl, or R^3 and R^4 taken together are 1,8-naphthylylene, and both R^2 and R^5 are 2,6-diisopropylphenyl.
- 43. The process as recited in claim 37 used to 10 make a block polymer.
 - 44. The process as recited in claim 37 wherein:
 M is Ti(IV), Q and S are chloride, and y and z are
 2;
 - M is Zr(IV), Q and S are chloride, and y and z are
- M is Co(II), Q and S are promide, and y and z are
 1;
 - M is Fe(II), Q and S are chloride, and y and z are 1;
- 20 M is Sc(III), Q and S are chloride, y is 1 and z is 2;
 - M is Ni(II), Q and s are bromide or chloride, and y and z are 1;
 - M is Pd(II), Q and S are methyl, and y and z are
- M is Pd(II), Q and S are chloride, and y and z are

 1;
 - M is Ni(I), Q is methyl, chloride, bromide, iodide or acetylacetonate, y is 1, and z is 0;
- 30 M is Pd(II), Q is methyl and S is chloride, and y and z are 1; or
 - M is Ni(II) \neq Q and S are methyl, and y and z are 1.
- 45. The process as recited in claim 37 wherein ethylene and propylene are the monomers.
 - 46. The process as recited in claim 37 wherein said monomers are part of a crude butenes stream.

15

20

25

47. The process as recited in claim 37 wherein R^2 and R^5 are each independently hydrocarbyl, provided that the carbon atom bound to the imino nitrogen atom has at least two carbon atoms bound to it; R^6 and R^4 are each independently hydrogen, hydrocarbyl, or R^3 and R^4 taken together are hydrocarbylene to form a carbocyclic ring.

48. The process as recited in claim 37 wherein said monomer comprises cyclopentene.

49. A process for the production of polyolefins, comprising, contacting, at a temperature of about - 100°C to about +200°C, one or more monomers selected from the group consisting of ethylene, an olefin of the formula R¹⁷CH=CH₂ or R¹⁷CH=CHR¹⁷, cyclobutene, cyclopentene, substituted norbornene, and norbornene; and a compound of the formula

$$R^3$$
 R^2
 R^3
 R^4
 R^2
 R^3
 R^4
 R^3
 R^4
 R^4
 R^5
 R^5
 R^5
 R^5
 R^7
 R^7

wherein: R^2 and R^5 are each independently hydrocarbyl or substituted hydrocarbyl, provided that the carbon atom bound to the imino nitrogen atom has at least two carbon atoms bound to it;

Ř⁵ (VII)

¹ 116

10

20

30

35

R³ and R⁴ are each independently hydrogen, hydrocarbyl, substituted hydrocarbyl, or R3 and R4 taken together are hydrocarbylene or substituted hydrocarbylene to form a carbocyclic ring;

T is hydrogen, hydrocarbyl not containing olefinic or acetylenic bonds, R¹⁵C(=0) - or R¹⁵OC(=0) -;

Z is a neutral Lewis base wherein the donating atom is nitrogen, sulfur or oxygen, provided that if the donating atom is nitrogen then the pka of the conjugate acid of that compound is less/than about 6;

X is a weakly coordinating anion;

R¹⁵ is hydrocarbyl not containing olefinic or acetylenic bonds;

each R17 is independently hydrocarbyl or substituted hydrocarbyl provided that any olefinic bond 15 in said olefin is separated from any other olefinic bond or aromatic ring by a quaternary carbon atom or at least two saturated carbon atoms;

M is Ni(II) or Pd(II/); each R16 is independently hydrogen or alkyl containing 1 to 10 carbon atoms

n is 1, 2, or 3;

R⁸ is hydrocarbyl and T² is hydrogen, hydrocarbyl not containing olefinic or acetylenic bowds, hydrocarbyl substituted 25 with keto or ester groups but not containing olefinic or acetylenic bonds, $R^{15}Q(=0)$ - or $R^{15}OC(=0)$ -;

provided that:

when M is Pd, \sqrt{r} (II) or (VII) are present, a diene is not present; And

when norborneme or substituted norbornene is used no other monomer is present.

50. The process as recited in claim 49 wherein said monomer is ethylene only.

51. The process as recited in claim 49 wherein said monomer is an/α -olefin only.

52. The process as recited in claim 51 wherein said α -olefin is propylene.

15

25

30

53. The process as recited in claim 49 wherein said compound is (II), (IV) or (VII), M is Pd(II), and a comonomer selected from the group consisting of: a compound of the formula $CH_2=CH(CH_2)_mCO_2R^1$, wherein R^1 is hydrogen or, hydrocarbyl or substituted hydrocarbyl containing 1 to 10 carbon atoms, and m is 0 or an integer of 1 to 16; CO; and a vinyl ketone, is also present.

54. The process as recited in claim 53 wherein m is 0, and R^1 is hydrocarbyl or substituted hydrocarbyl.

55. The process as recited in claim 49 done in the presence of a solvent.

56. The process as recited in claim 49 done in the absence of a solvent.

57. The process as recited in claim 49 wherein R^3 and R^4 are each independently hydrogen or methyl, or R^3 and R^4 taken together are 1,8-naphthylylene, and both R^2 and R^5 are 2,6-diisopropylphenyl.

58. The process as recited in claim 49 used to

20 make a block polymer.

59. The process as reciped in claim 49 wherein X is BAF, SbF₆, PF₆, or BF₄

60. The process as recited in claim 57 wherein X is BAF, SbF₆, PF₆, or BF₄

61. The process as recited in claim 60 wherein a monomer is ethylene or propylene.

62. The process as recited in claim 49 wherein the monomers are ethylene and propylene.

63. The process as recited in claim 49 wherein said monomers are part of a crude butenes stream.

and R^5 are each independently hydrocarbyl, provided that the carbon atom bound to the imino nitrogen atom has at least two carbon atoms bound to it; R^3 and R^4 are each independently hydrogen, hydrocarbyl, or R^3 and R^4 taken together are hydrocarbylene to form a carbocyclic ring.

65. A process for the production of polyolefins, comprising contacting, at a temperature of about -100°C to about +200°C, one or more monomers selected from the group consisting of ethylene, an olefin of the formula R¹⁷CH=CH₂ or R¹⁷CH=CHR¹⁷, cyclobutene, cyclopentene/ substituted norbornene, and norbornene; with a compound of the formula

R²⁰

(XVIII)

or

(XVII)

$$\begin{array}{c|c}
R^{20} \\
H \\
R^{21} = N \\
N \\
X
\end{array}$$

$$\begin{array}{c|c}
T^1 \\
M \\
Z \\
O \\
H \\
R^{23}
\end{array}$$

(XIII)

10

15

20

wherein:

R44 is hydrocarbyl or substituted hydrocarbyl, and R28 is hydrogen, hydrocarbyl or substituted hydrocarbyl or R^{44} and R^{28} taken together form a ring; R45 is hydrocarbyl or substituted hydrocarbyl, and R²⁹ is hydrogen, substituted hydrocarbyl or hydrocarbyl, or R^{45} and R^{29} taken together form a ring; each R30 is/independently hydrogen, substituted hydrocarbyl or hydrocarbyl or two of R^{30} taken together form a ring; R^{20} and R^{23} are independently hydrocarbyl or substituted hydrocarbyl;

20

25

30

R²¹ and R²² are each in independently hydrogen hydrocarbyl or substituted hydrocarbyl;

n is 2 or 3;

T¹ is hydrogen, hydrocarbyl not containing olefinic or acetylenic bonds, R¹⁵C(=0) - or R¹⁵OC(=0) -;

M is Ti, Zr, Sc, Cr, a rare earth metal, V, Fe, Co, Ni or Pd the m oxidation state;

for (XVII), y + z = m;

for (XIII), m is 2;

Q is alkyl, hydride, chloride, iodide, or bromide;

S is alkyl, hydride, chloride, jodide, or bromide;

T² is hydrogen, hydrocarbyl not containing olefinic or acetylenic bonds, hydrocarbyl substituted with keto or ester groups but not containing olefinic or acetylenic bonds, R¹⁵C(=0) - or R¹⁵OC(=0) -;

Z is a neutral Lewis base/wherein the donating atom is nitrogen, sulfur or oxygen, provided that if the donating atom is nitrogen then the pKa of the conjugate acid of that compound is less than about 6; and

X is a weakly coordinating anion; and provided that:

when said compound is (XVII) M is not Pd; and except when M is Pd, when both Q and S are each independently chloride, promide or iodide W is capable of transferring a hydride or alkyl group to M.

- 66. The process as recited in claim 65 wherein said monomer is ethylene only.
 - 67. The process as recited in claim 65 wherein said monomer is an α -olefin only.
 - 68. The process/as recited in claim 67 wherein said α -olefin is propylene.
- 35 69. The process as recited in claim 66 wherein M is Pd(II) and one or more comonomer is selected from the group consisting of: a compound of the formula $CH_2=CH\left(CH_2\right)_mCO_2R^1, \text{ wherein } R^1 \text{ is hydrogen or, hydrocarbyl}$

15

20

25

or substituted hydrocarbyl containing 1 to 10 carbon atoms, and m is 0 or an integer of 1 to 16; CO; and a vinyl ketone is also present.

70. The process as recited in claim 69 wherein m is 0, and \mathbb{R}^1 is hydrocarbyl or substituted hydrocarbyl.

- 71. The process as recited in claim 65 done in the presence of a solvent.
- 72. The process as recited in claim 65 done in the absence of a solvent.
- 73. The process as recited in claim 65 used to make a block polymer.
 - 74. The process as recited in claim 65 wherein X is BAF, SbF₆, PF₆, or BF₄.
 - 75. The process as recited in claim 74 wherein a monomer is ethylene or propylene.
 - 76. The process as recited in claim 75 wherein the monomers are ethylene and propylene.
 - 77. The process as recited in claim 65 wherein said monomers are part of a crude butenes stream.

78. The process as recited in claim 65 wherein:

R⁴⁴ is hydrocarbyl, and R²⁸ is hydrogen or

hydrocarbyl, or R⁴⁴ and R⁴⁸ taken together form a ring;

R⁴⁵ is hydrocarbyl, and R²⁹ is hydrogen or

hydrocarbyl, or R⁴⁵ and R²⁹ taken together form a ring;

each R³⁰ is independently hydrogen or hydrocarbyl, or two of R³⁰ taken together form a ring;

R²¹ and R²² are each in independently hydrogen

or hydrocarbyl; and R^{20} and R^{23} are independently hydrocarbyl.

79. A process for the production of polyolefins, comprising contacting, at a temperature of about -100°C to about +200°C, one or more monomers selected from the group consisting of ethylene, an olefin of the formula R17CH=CH2 or R17CH=CHR17, cyclobutene, cyclopentene, substituted norbornene, and norbornene; with a compound of the formula

15

20

25

$$R^{20}$$
 R^{21}
 R^{21}
 R^{21}
 R^{21}
 R^{22}
 R^{22}
 R^{23}

(XVIII)

wherein:

 ${\rm R}^{20}$ and ${\rm R}^{23}$ are independently hydrocarbyl or substituted hydrocarbyl;

 R^{21} and R^{22} are each in independently hydrogen, hydrocarbyl or substituted hydrocarbyl

X is a weakly coordinating anion;

each R¹⁷ is independently hydrocarbyl or substituted hydrocarbyl provided that any olefinic bond in said olefin is separated from any other olefinic bond or aromatic ring by a quaternary carbon atom or at least two saturated carbon atoms;

M is Ni(II) or Pa(II);

 T^2 is hydrogen, hydrocarbyl not containing olefinic or acetylenic bonds, hydrocarbyl substituted with keto or ester groups but not containing olefinic or acetylenic bonds, $R^{15}C(-0)$ - or $R^{15}OC(-0)$ -;

and provided that

when M is Pd a diene is not present; and when norbornene or substituted norbornene is used no other monomer is present.

80. The process as recited in claim 79 wherein said monomer is ethylene only.

81. The process as recited in claim 79 wherein said monomer is an α -olefin only.

82. The process as recited in claim 81 wherein said α -olefin is propylene.

83. The process as recited in claim 79 wherein T^2 is methyl; R^{20} and R^{23} are independently hydrocarbyl; and R^{21} and R^{22} are each in independently hydrogen or hydrocarbyl.

84. A process for the production for polyolefins, comprising contacting, at a temperature of about/-100°C to about +200°C,

a first compound W, which is a neutral Lewis acid capable of abstracting either Q or S to form WQ or WS', provided that the anion formed is a weakly coordinating anion; or a cationic Lewis or Bronsted acid whose counterion is a weakly coordinating anion;

a second compound of the formula

10

15

20

25

and one or more monomer's selected from the group consisting of ethylene, an olefin of the formula R¹⁷CH=CH₂ or R¹⁷CH=CHR¹⁷, cyclopentene, substituted norbornene, pr narbornene;

M is Ti, Zr, V, Cr/ a rare earth metal, Co, Fe, wherein:

Sc, or Ni, of oxidation state m; R44 is hydrocarbyl or substituted hydrocarbyl, and R^{28} is hydrogen, substituted hydrocarbyl or hydrocarbyl, or R^{44} and R^{28} taken together form a ring;

R45 is hydrocartyl or substituted hydrocarbyl,

and R29 is hydrogen, substituted hydrocarbyl or

hydrocarbyl, or R^{45} and R^{29} taken together form a ring; each R^{30} is/independently hydrogen, substituted

hydrocarbyl or hydrocarbyl, or two of R30 taken together form a ring;

n is 2 of 3;

y and z/are positive integers; 30

y+z =

 $each/R^{17}$ is independently hydrocarbyl or substituted hydrocarbyl provided that any olefinic bond

35

in said olefin is separated from any other olefinic bond or aromatic ring by a quaternary carbon atom or at least two saturated carbon atoms;

Q is alkyl, hydride, chloride, iodide, or 5 bromide;

S is alkyl, hydride, chloride, iodide, or bromide; and

provided that;

when norbornene or substituted norbornene is 10 present, no other monomer is present.

- 85. The process as recited in claim 84 wherein R^{28} , R^{29} , and each of R^{30} are hydrogen.
- 86. The process as recited in/claim 84 wherein said monomer is ethylene only.
- 15 87. The process as recited in claim 84 wherein said monomer is an α -olefin only.
 - 88. The process as recited in claim 87 wherein said α -olefin is propylene.
- 89. The process as recited in claim 84 done in the 20 presence of a solvent.
 - 90. The process as recated in claim 84 wherein both R^{44} and R^{45} are 2,4,6 trimethylphenyl.
 - 91. The process as recited in claim 84 used to make a block polymer.
 - 92. The process as recited in claim 90 wherein a monomer is ethylene or propylene.
 - 93. The process as recited in claim 84 wherein:
 - M is Ti(IV), Q and S are chloride, and y and z are 2;
- M is Zr(IV), Q and S are chloride, and y and z are 2;
 - M is Co(II), ϕ and S are bromide, and y and z are 1;
 - M is Fe(II) / Q and S are chloride, and y and z are
 1;
 - M is $Sc(III_1^f)$, Q and S are chloride, y is 1 and z is 2;

20

25

30

M is Ni(II), Q and S are bromide or chloride, and y and z are 1;

M is Pd(II), Q and S are chloride, and y and z are

1;
5 M is Pd(II), Q and S are methyl, and y and z are

1;
 M is Ni(I), Q is methyl, chloride, bromide, iodide
or acetylacetonate, y is 1, and z is 0;

M is Pd(II), Q is methyl and S is chloride, and y and z are 1; or

M is Ni(II), Q and S are methyl, and y and z are

94. The process as recited in claim 84 wherein ethylene and propylene are the monomers.

95. The process as recited in claim 84 wherein said monomers are part of a crude butenes stream.

96. The process as recited in claim 84 wherein:

R⁴⁴ is hydrocarbyl, and R²⁸ is hydrogen or

hydrocarbyl, or R^{44} and R^{28} taken together form a ring; R^{45} is hydrocarbyl, and R^{29} is hydrogen or hydrocarbyl, or R^{45} and R^{29} taken together form a ring;

each R^{30} is independently hydrogen or hydrocarbyl, or two of R^{30} taken together form a ring.

97. A process for the production of polyolefins, comprising, contacting, at a temperature of about - 100°C to about +200°C, one or more monomers selected from the group consisting of ethylene, an olefin of the formula R¹ CH=CH₂ or R¹⁷CH=CHR¹⁷, cyclobutene,

cyclopentene, substituted norbornene, and norbornene; optionally a source of X^- , and a compound of the formula

15

20

25

30

35

wherein:

R² and R⁵ are each independently hydrocarbyl or substituted hydrocarbyl, provided that the carbon atom bound directly to the imino nitrogen atom has at least two carbon atoms bound to it;

R³ and R⁴ are each independently hydrogen, hydrocarbyl, substituted hydrocarbyl, or R³ and R⁴ taken together are hydrocarbylene or substituted hydrocarbylene to form a carbocyclic ring;

each R¹⁷ is independently hydrocarbyl or substituted hydrocarbyl provided that R¹⁷ contains no olefinic bonds;

 T^1 is hydrogen, hydrocarbyl not containing olefinic or acetylenic bonds, $R^{15}\mathcal{O}(=0)$ - or $R^{15}\mathcal{O}(=0)$ -; R^{15} is hydrocarbyl not containing olefinic or acetylenic bonds;

E is halogen or -OR18/;

 $\ensuremath{\mathbb{R}}^{18}$ is hydrocarbyl not containing olefinic or acetylenic bonds; and

X is a weakly condinating anion;

provided that when norbornene or substituted norbornene is present no other monomer is present.

98. The process as recated in claim 97 wherein said monomer is ethylene only.

99. The process as recited in claim 97 wherein said monomer is an $\alpha\text{-olefin}$ only.

100. The process as recited in claim 99 wherein said $\alpha\text{-ole}\textsc{fin}$ is propylene.

101 The process as recited in claim 97 wherein E is chlorine.

 $_{102}^{102}.$ The process as recited in claim 97 wherein T^{1} is alkyl.

103. The process as recited in claim 97 done in the presence of a solvent.

/ 104. The process as recited in claim 98 wherein E is chlorine and T^1 is alkyl.


10

15

20

25

30



106. The process as recited in claim 97 used to make a block polymer.

107. The process as recited in claim 105 wherein X is BAF, SbF₆, PF₆, or BF₄.

108. The process as recited in claim 107 wherein a monomer is ethylene or propylene.

109. The process as recited in claim 97 wherein the monomers are ethylene and propylene.

110. The process as recited in claim 97 wherein said monomers are part of a crude butenes stream.

and R⁵ are each independently hydrocarbyl or substituted hydrocarbyl, provided that the carbon atom bound directly to the imino nitrogen atom has at least two carbon atoms bound to it; and R³ and R⁴ are each independently hydrogen, hydrocarbyl, substituted hydrocarbyl, or R³ and R⁴ taken together are hydrocarbylene or substituted hydrocarbylene to form a carbocyclic ring.

112. A process for the polymerization of olefins, comprising, contacting, at a temperature of about - 100°C to about +200°C:

a first compound W, which is a neutral Lewis acid capable of abstracting either Q or S to form WQ or WS, provided that the anion formed is a weakly coordinating anion; or a cationic Lewis or Bronsted acid whose counterion is a weakly coordinating anion; a second compound of the formula

$$\begin{array}{c|c}
R^3 & R^2 \\
 & N \\
 & N \\
 & N \\
 & N \\
 & S \\
 & & R^5
\end{array}$$

15

20

and one or more monomers selected from the group consisting of ethylene, an olefin of the formula R¹⁷CH=CH₂ or R¹⁷CH=CHR¹⁷, 4-vinylcyclohexene, cyclobutene, cyclopentene, substituted norbornene, and

wherein:

norbornene;

M is Ni(II), Co(II), Fe(II) of Pd(II);

R² and R⁵ are each independently hydrocarbyl or substituted hydrocarbyl, provided that the carbon atom bound to the imino nitrogen atom has at least two carbon atoms bound to it;

R³ and R⁴ are each independently hydrogen, hydrocarbyl, substituted hydrocarbyl, or R3 and R4 taken together are hydrocarbylene or substituted hydrocarbylene to form a carbocyclic ring;

each R17 is independently hydrocarbyl or substituted hydrocarbyl provided that any olefinic bond in said olefin is separated from any other olefinic bond or aromatic ring by a quaternary carbon atom or at least two saturated carbon atoms;

Q is alky, Avdride, chloride, iodide, or

bromide;

S is alkyl, hydride, chloride, iodide, or

bromide; and 25

provided that:

when norbornene or substituted norbornene is present, no other monomer is present, and further provided that when 4-vinylcyclohexene is present M is

30 Ni;

when M is Pd a diene is not present; and except when M is Pd, when both Q and S are each independently chloride, bromide or iodide W is capable of/transferring a hydride or alkyl group to M.

113. The process as recited in claim 112 wherein 35 said monomer is ethylene only.

114. The process as recited in claim 112 wherein said monomer is an α -olefin only.

428

15

25

35

115. The process as recited in claim 114 wherein said α -olefin is propylene.

116. The process as recited in claim 112/done in the presence of a solvent.

117. The process as recited in claim 112 wherein \mathbb{R}^3 and \mathbb{R}^4 are each independently hydrogen or methyl or both of \mathbb{R}^3 and \mathbb{R}^4 taken together are 1.8-naphthylylene, and both \mathbb{R}^2 and \mathbb{R}^5 are 2.6-diisopropylphenyl.

118. The process as recited in claim 112 used to make a block polymer.

119. The process as recited in claim 112 wherein a monomer is ethylene or propylene.

120. The process as recited in claim 112 wherein the molar ratio of said first compound: said second compound (I) is about 5 to about 1000.

121. The process as recited in claim 112 wherein the molar ratio of said first compound: said second compound (I) is about 10 to about 100.

122. The process as recited in claim 112 wherein said first compound is R⁹AlCl₂, R⁹₂AlCl, R⁹₃Al₂Cl₃, or an alkylaluminoxane in which the alkyl group has 1 to 4 carbon atoms, and wherein R⁹ is alkyl containing 1 to 4 carbon atoms.

123. The process as recited in claim 120 wherein said first compound is R⁹AlCl₂, R⁹₂AlCl, R⁹₃Al₂Cl₃, or an alkylaluminoxane in which the alkyl group has 1 to 4 carbon atoms, and wherein R⁹ is alkyl containing 1 to 4 carbon atoms.

124. The process as recited in claim 112 wherein 30 the monomer comprises cyclopentene.

125. The process as recited in claim 112 wherein said monomers are part of a crude butenes stream.

126. The process as recited in claim 112 wherein \mathbb{R}^2 and \mathbb{R}^5 are each independently hydrocarbyl, provided that the carbon atom bound to the imino nitrogen atom has at least two carbon atoms bound to it; and \mathbb{R}^3 and \mathbb{R}^4 are each independently hydrogen, hydrocarbyl, or \mathbb{R}^3

429

and R^4 taken together are hydrocarbylene to form a carbocyclic ring.

127. A polymerization process, comprising contacting a compound of the formula $[Pd(R^{13}CN)_4]X_2$, or a combination of $Pd[OC(0)R^{40}]_2$ and HX, with a compound of the formula

10

and one or more monomers selected from the group consisting of ethylene, an olefin of the formula $R^{17}CH=CH_2$ or $R^{17}CH=CHR^{17}$, cyclopentene, cyclobutene, substituted norbornene and norbornene, wherein:

15

 R^2 and R^5 are each independently hydrocarbyl or substituted hydrocarbyl, provided that the carbon atom bound to the imino nitrogen atom has at least two carbon atoms bound to it;

20

R³ and R⁴ are each independently hydrogen, hydrocarbyl, substituted hydrocarbyl, or R³ and R⁴ taken together are hydrocarbylene or substituted hydrocarbylene to form a carbocyclic ring;

each R¹⁷ is independently hydrocarbyl or substituted hydrocarbyl providedR¹⁷ contains no olefinic bonds;

25

 R^{13} is hydrocarbyl; R^{40} is hydrocarbyl or substituted hydrocarbyl;

and /

X is a weakly coordinating anion;

provided that when norbornene or substituted
porbornene, is present no other monomer is present.

30

128. The process as recited in claim 127 wherein said monomer is ethylene only.

10

15

20

25

30

35

129. The process as recited in claim 127 wherein said monomer is an α -olefin only.

130. The process as recited in claim 128 wherein said $\alpha\text{-olefin}$ is propylene.

one or more comonomer selected from the group consisting of: a compound of the formula $CH_2=CH\left(CH_2\right)_mCO_2R^1$, wherein R^1 is hydrogen or, hydrocarbyl or substituted hydrocarbyl containing 1 to 10 carbon atoms, and m is 0 or an integer of 1 to 16; CO; and a vinyl ketone is also present.

132. The process as recited in claim 131 wherein m^2 is 0, and R^1 is hydrocarbyl or substituted hydrocarbyl.

133. The process as recited in claim 127 done in the presence of a solvent.

134. The process as recited in claim 127 wherein R^3 and R^4 are each independently hydrogen or methyl or both R^3 and R^4 taken together are 1,8-naphthylylene, and both R^2 and R^5 are 2,6-diisopropylphenyl.

135. The process as recited in claim 127 used to make a block polymer

136. The process as recited in claim 127 wherein X is BAF, ${\rm SbF_6}$, ${\rm PF}$, or ${\rm BF_4}$

137. The process as recited in claim 134 wherein X is BAF or BF4.

138. The process as recited in claim 137 wherein a monomer is ethylene or propylene.

139. The process as recited in claim 127 wherein the monomers are ethylene and propylene.

140. The process as recited in claim 127 wherein said monomers are part of a crude butenes stream.


141. The process as recited in claim 127 wherein R^2 and R^5 are each independently hydrocarbyl, provided that the carbon atom bound to the imino nitrogen atom has at least two carbon atoms bound to it; and R^3 and R^4 are each independently hydrogen, hydrocarbyl, or R^3 and R^4 taken together are hydrocarbylene to form a carbocyclic ring.

431


142. A polymerization process, comprising, contacting:

a Ni[0], Pd[0] or Ni[I] compound containing a ligand which may be displaced by a ligand of the formula (VIII), (XXX), (XXXII) or (XXIII);

a second compound of the formula



10



(XXIII)

$$R^{20}$$
 R^{21}
 R^{21}
 R^{22}
 R^{22}
 R^{23}

(XXXII)

5

10

25

30

an oxidizing agent;

a source of a relatively weakly coordinati: anion;

and one or more monomers selected from the group consisting of ethylene, an olefin of the for R¹⁷CH=CH₂ or R¹⁷CH=CHR¹⁷, cyc/opentene, cyclobutene, substituted norbornene, and norbornene;

wherein:

R² and R⁵ are each independently hydrocarb substituted hydrocarbyl/ provided that the carbon bound to the imino nit togen atom has at least two carbon atoms bound to/it;

 R^3 and R^4 are eagh independently hydrogen, hydrocarbyl, substituted bydrocarbyl or R^3 and R^4 15 together are hydrodarby ene or substituted hydrocarbylene to form a ring;

each R^{17}/is independently hydrocarbyl or substituted hydrocarbyl provided that any olefini in said olefin As separated from any other olefin 20 bond or aromat/c ring by a quaternary carbon ator least two saturated carbon atoms;

 $\operatorname{each}/R^{31}$ is independently hydrogen, hydro or substituted hydrocarbyl;

R44/is hydrocarbyl or substituted hydroca and R²⁸ is/hydrogen, hydrocarbyl or substituted hydrocarbyl or R44 and R28 taken together form a k^{45} is hydrocarbyl or substituted hydrocarbyl and R²⁹ is hydrogen, substituted hydrocarbyl or hydrocarbyl, or R^{45} and R^{29} taken together form a kly coordinating ected from the fingof the formula , cyclobutene, ne ;[[ntly hydrocarbyl or hat the carbon atom s all least two ently hydrogen 1 or R3 and R taken tituted: hydrocarbyl or hat any definic bond ny other/olefinic ary carbon atom or at nydrogen, hydrocarbyl tituted hydrocarbyl, r substituted gether form a ring; stituted hydrocarbyl, ydrocarbyl or together form a ring;

s independently hydrogen, substituted drocarbyl, or two of R30 taken ing; ⁷ are each independently hydrocarbyl drocarbyl, provided that the carbon imino nitrogen atom has at least two i to it; 3; 'are each independently hydrogen, ubstituted hydrocarbyl; are independently hydrocarbyl or carbyl; are each in independently hydrogen, estituted hydrocarbyl; and -; ene or substituted norbornene is monomer is present; compound is used, a diene is not cond compound is (XXX) only an Ni[0] is used. ess as recited in claim 142 wherein hylene only. ess as recited in claim 142 wherein α-olefin only. less as recited in claim 144 wherein ropylene. ess as recited in claim 142 done in solvent. ess as recited in claim 142 used to er. ess as /recited in claim 142 wherein thylene and propylene. ess as recited in claim 142 wherein part of a crude butenes stream. ess as recited in claim 142 wherein: re each independently hydrocarbyl, carpon atom bound to the imino

(XXXII)

5

10

15

20

25

an oxidizing agent;

a source of a relatively weakly coordinating anion;

and one or more monomers selected from the group consisting of ethylene, an olefin of the formula R¹⁷CH=CH₂ or R¹⁷CH=CHR¹⁷, cyclopentene, cyclobutene, substituted norbornene, and norbornene;

wherein:

R² and R⁵ are each independently hydrocarbyl or substituted hydrocarbyl, provided that the carbon atom bound to the imino nitrogen atom has at least two carbon atoms bound to it.

R³ and R⁴ are each independently hydrogen, hydrocarbyl, substituted hydrocarbyl or R³ and R⁴ taken together are hydrocarbylene or substituted hydrocarbylene to form a ring;

each R¹⁷ is independently hydrocarbyl or substituted hydrocarbyl provided that any olefinic bond in said olefin is separated from any other olefinic bond or aromatic ring by a quaternary carbon atom or at least two saturated carbon atoms;

each R³¹ is independently hydrogen, hydrocarbyl or substituted hydrocarbyl;

 R^{44} is hydrocarbyl or substituted hydrocarbyl, and R^{28} is hydrogen, hydrocarbyl or substituted hydrocarbyl or R^{44} and R^{28} taken together form a ring;

 R^{45} is hydrocarbyl or substituted hydrocarbyl, and R^{29} is hydrogen, substituted hydrocarbyl or hydrocarbyl, or R^{45} and R^{29} taken together form a ring;

10

1.5

20

25

30

35

each R³⁰ is independently hydrogen, substituted hydrocarbyl or hydrocarbyl, or two of R³⁰ taken together form a ring;

 R^{46} and R^{47} are each independently hydrocarbyl or substituted hydrocarbyl, provided that the carbon atom bound to the imino nitrogen atom has at least two carbon atoms bound to it;

n is 2 or 3;

R⁴⁸ and R⁴⁹ are each independently hydrogen, hydrocarbyl, or substituted hydrocarbyl;

R²⁰ and R²³ are independently hydrocarbyl or substituted hydrocarbyl;

R²¹ and R²² are each in independently hydrogen, hydrocarbyl or substituted hydrocarbyl; and

provided that;

when norbornene or substituted norbornene is present, no other monomer is present;

when a Pd[0] compound is used, a diene is not present; and

when said second compound is (XXX) only an Ni[0] or Ni[I] compound is used.

143. The process as recited in claim 142 wherein said monomer is ethylene only.

144. The process as recited in claim 142 wherein said monomer is an α -olefin only.

145. The process as recited in claim 144 wherein said α -olefan is propylene.

146. The process as recited in claim 142 done in the presence of a solvent.

147/ The process as recited in claim 142 used to make a plock polymer.

148. The process as recited in claim 142 wherein the monomers are ethylene and propylene.

149. The process as recited in claim 142 wherein said monomers are part of a crude butenes stream.

150. The process as recited in claim 142 wherein:

R² and R⁵ are each independently hydrocarbyl,

provided that the carbon atom bound to the imino

nitrogen atom has at least two carbon a toms bound to it; R³ and R⁴ are each independently hydrogen, hydrocarbyl, or R³ and R⁴ taken together are hydrocarbylene to form a ring; each R¹⁷ is independently/hydrocarbyl provided that any olefinic bond in said olefin is separated from any other olefinic bond or aromatic ring by a quaternary carbon atom or at least two saturated carbon 10 atoms; each R31 is independently hydrogen or hydrocarbyl; R44 is hydrocarbyl, and R28 is hydrogen or hydrocarbyl or R44 and R28 taken together form a ring; R45 is hydrocarby, and R29 is hydrogen, or 15 hydrocarbyl, or R45 and R29 taken together form a ring; each R³⁰ is independently hydrogen or hydrocarbyl, or two of/ R^{30} taken together form a ring; R^{46} and R^{47} are each independently hydrocarbyl, provided that the carbon atom bound to the imino 20 nitrogen atom has at least two carbon atoms bound to it; R48 and R49 are each independently hydrogen or hydrocarbyl; R²⁰ and R²³ are independently hydrocarbyl; and 25 R²¹ and R²² are each in independently hydrogen or hydrocarbyl. 151. The process as recited in claim 142 wherein said olefin comprises cyclopentene. 152. A polymerization process, comprising, 30 contacting a Ni[0] complex containing a ligand or


ligands which may be displaced by (VIII), oxygen, an alkyl aluminum compound, and a compound of the formula

15

20

25

30



and one or more monomers selected from the group consisting of ethylene, an olefin of the formula R¹⁷CH=CH₂ or R¹⁷CH=CHR¹⁷, cyclopentene, cyclobutene, substituted norbornene, and norbornene; wherein:

R² and R⁵ are each independently hydrocarbyl or substituted hydrocarbyl, provided that the carbon atom bound to the imino nitrogen atom has at least two carbon atoms bound to it;

R³ and R⁴ are each independently hydrogen, hydrocarbyl, substituted hydrocarbyl or R³ and R⁴ taken together are hydrocarbylene or substituted hydrocarbylene to form a ring; and

each R¹⁷ is independently hydrocarbyl or substituted hydrocarbyl provided that any olefinic bond in said olefin is separated from any other olefinic bond or aromatic ring by a quaternary carbon atom or at least two saturated carbon atoms;

provided that, when norbornene or substituted norbornene is present, no other monomer is present.

153. The process as recited in claim 152 wherein R² and R⁵ are each independently hydrocarbyl, provided that the carbon atom bound to the imino nitrogen atom has at least two carbon atoms bound to it; and R³ and R⁴ are each independently hydrogen, hydrocarbyl, or R³ and R⁴ taken together are hydrocarbylene to form a carbocyclic ring.

154. The process as recited in claim 152 wherein said Ni[0] complex is a 1,5-cyclooctadiene complex.

155. The process as recited in claim 152 wherein said monomer is ethylene only.

15.

20

25

156. The process as recited in claim 152 wherein said olefin comprises cyclopentene.

157. The process as recited in claim 152 wherein said monomer is an α -olefin only.

158. The process as recited in claim 157 wherein said $\alpha\text{-olefin}$ is propylene.

159. The process as recited in claim 152 done in the presence of a solvent.

160. The process as recited in claim 156 used to 10 make a block polymer.

161. The process as recited in claim 152 wherein the monomers are ethylene and propylene.

162. The process as recited in claim 152 wherein said monomers are part of a crude butenes stream.

163. A polymerization process, comprising, contacting oxygen and an alkyl aluminum compound, or a compound of the formula HX, and a compound of the

and one or more monomers selected from the group consisting of ethylene, an olefin of the formula $R^{17}CH=CH_2$ or $R^{17}CH=CHR^{17}$, cyclopentene, cyclobutene, substituted morbornene, and norbornene; wherein:

 ${\mbox{R}}^2$ and ${\mbox{R}}^5$ are each independently hydrocarbyl or substituted hydrocarbyl, provided that the carbon atom

25

30

bound to the imino nitrogen atom has at least two carbon atoms bound to it;

 R^3 and R^4 are each independently hydrogen, hydrocarbyl, substituted hydrocarbyl or R^3 and R^4 taken together are hydrocarbylene or substituted hydrocarbylene to form a ring; and

each R¹⁷ is independently hydrocarbyl or substituted hydrocarbyl provided that any olefinic bond in said olefin is separated from any other olefinic bond or aromatic ring by a quaternary carbon atom or at least two saturated carbon atoms;

X is a weakly coordinating anion; and provided that, when norbornene or substituted norbornene is present, no other monomer is present.

164. The process as recited in claim 163 wherein R² and R⁵ are each independently hydrocarbyl, provided that the carbon atom bound to the imino nitrogen atom has at least two carbon atoms bound to it; and R³ and R⁴ are each independently hydrogen, hydrocarbyl, or R³ and R⁴ taken together are hydrocarbylene to form a carbocyclic ring.

165. The process as recited in claim 142 wherein said Ni[0] compound is bis(1,5cycloocatdiene)nickel or bis(o-tolylphosphito)nickel(ethylene) or said Pd[0] compound is tris(dibenzylideneacetone)dipalladium[0].

166. The process as recited in claim 163 wherein said monomer is ethylene only.

167. The process as recited in claim 163 wherein said olefin comprises cyclopentene.

168. The process as recited in claim 163 wherein said monomer is an α -olefin only.

169. The process as recited in claim 168 wherein said α -oleft in is propylene.

170. The process as recited in claim 163 done in the presence of a solvent.

171. The process as recited in claim 163 used to make a block polymer.

10

172. The process as recited in claim 163 wherein the monomers are ethylene and propylene.

173. The process as recited in claim 163 wherein said monomers are part of a crude bytenes stream.

174. The process as recited in claim 164 wherein said olefin comprises cyclopentene.

175. The process as recited in claim 164 wherein said monomer is ethylene only.

176. A polymerization process, comprising, contacting an Ni[0] complex containing a ligand or ligands which may be displaced by (VIII), HX or a Bronsted acidic solid, and a compound of the formula

15 (VIII)

20

25

30

and one or more monomers selected from the group consisting of ethylene, an olefin of the formula $R^{17}CH=CH_2$ or $R^{17}CH=CHR^{17}$, cyclopentene, cyclobutene, substituted norbornene, and norbornene; wherein:

 R^2 and R^5 are each independently hydrocarbyl or substituted hydrocarbyl, provided that the carbon atom bound to the imino mitrogen atom has at least two carbon atoms bound to it;

R³ and R⁴ are each independently hydrogen, hydrocarbyl, substituted hydrocarbyl or R³ and R⁴ taken together are hydrocarbylene or substituted hydrocarbylene to form a ring;

each R¹⁷ is independently hydrocarbyl or substituted hydrocarbyl provided that any olefinic bond in said olefin is separated from any other olefinic bond or aromatic ring by a quaternary carbon atom or at least two saturated carbon atoms; and

X is a weakly coordinating anion;

15

20

25

35

provided that, when norbornene or substituted norbornene is present, no other monomer is present.

177. The process as recited in claim 176 wherein R² and R⁵ are each independently hydrocarbyl, provided that the carbon atom bound to the imino nitrogen atom has at least two carbon atoms bound to it; and R3 and R4 are each independently hydrogen, hydrocarbyl, or R3 and R4 taken together are hydrocarbylene to form a carbocyclic ring.

178. The process as recited in claim 176 wherein said Ni[0] complex is bis(1,5-cy/loocatidene)nickel or bis(o-tolylphosphito)nickel(ethylene)

179. The process as recited in claim 176 wherein said monomer is ethylene only /

180. The process as recited in claim 176 wherein said olefin comprises cyclopentene.

181. The process as recited in claim 176 wherein said monomer is an α -olefin only.

182. The process as recited in claim 181 wherein said α -olefin is propylene.

183. The process as necited in claim 176 done in the presence of a solvent

184. The process as pecited in claim 176 used to make a block polymer.

185. The process as recited in claim 176 wherein the monomers are ethylene and propylene.


186. The process as recited in claim 176 wherein said monomers are /part of a crude butenes stream.

187. A process for the polymerization of olefins, comprising, contacting, at a temperature of about 30 -100°C to about/+200°C:

a first compound W, which is a neutral Lewis acid capable ϕ f abstracting either Q or S to form WQor WS, provided that the anion formed is a weakly coordinating anion; or a cationic Lewis or Bronsted acid whose counterion is a weakly coordinating anion;

a second compound of the formula

440



and one or more monomers selected from the group consisting of ethylene, an olefin of the formula $R^{17}CH=CH_2$ or $R^{17}CH=CHR^{17}$, cyclobutene, cyclopentene, substituted norbornene, or norbornene;

wherein:

M is Ni(II) of Pd(II);

 R^{20} and R^{23} are independently hydrocarbyl or

substituted hydrocarbyl; 10

 R^{21} and R^{22} are each in independently hydrogen, hydrocarbyl or substituted hydrocarbyl;

each R17 is independently hydrocarbyl or substituted hydrocarbyl provided that any olefinic bond in said olefin is separated from any other olefinic bond or aromatic ring by a quaternary carbon atom or at least two saturated carbon atoms;

Q is alkyl, haride, chloride, iodide, or

bromide;

15

20

25

S is alkyl, hydride, chloride, iodide, or

bromide;

provided that;

when norbornene or substituted norbornene is present, no other monomer is present;

when M is Pd a diene is not present; and except when M is Pd, when both Q and S are each independently chloride, bromide or iodide W is capable of transferring a hydride or alkyl group to M.

188. The process as recited in claim 187 wherein said monomer is ethylene only. 30

441

15

20

25

30

189. The process as recited in claim 187 wherein said monomer is an α -olefin only.

190. The process as recited in claim 189 wherein said α -olefin is propylene.

191. The process as recited in claim 187 done in the presence of a solvent.

192. The process as recited in claim 187 used to make a block polymer.

193. The process as recited in claim 191 wherein a 10 monomer is ethylene or propylene.

194. The process as recited in claim 187 wherein the molar ratio of said first compound: said second compound (I) is about 5 to about 1000

195. The process as recited in claim 187 wherein the molar ratio of said first compound: said second compound (I) is about 10 to about 100.

196. The process as recited in claim 187 wherein the monomers are ethylene and propylene.

197. The process as recited in claim 187 wherein said monomers are part of a crude butenes stream.

198. The process as recited in claim 187 wherein R^{20} and R^{23} are independently hydrocarbyl; R^{21} and R^{22} are each in independently hydrogen or hydrocarbyl; and each R^{17} is independently hydrocarbyl provided that any olefinic bond in said olefin is separated from any other olefinic bond or aromatic ring by a quaternary carbon atom or at least two saturated carbon atoms.

199. A process for the polymerization of olefins, comprising, contacting, at a temperature of about - 100°C to about +200°C, a compound of the formula

442

20

25

and one or more monomers selected from the group consisting of ethylene, an olefin of the formula $R^{17}CH=CH_2$ or $R^{17}CH=CHR^{17}$, cyclopentene, cyclobutene, substituted norbornene, and norbornene; wherein:

 R^2 and R^5 are each independently hydrocarbyl or substituted hydrocarbyl, provided that the carbon atom bound to the imino nitrogen atom has at least two carbon atoms bound to it;

 R^3 and R^4 are each independently hydrogen, hydrocarbyl, substituted hydrocarbyl, or R^3 and R^4 taken together are hydrocarbylene or substituted hydrocarbylene to form a carbocyclic ring;

each R¹⁷ is independently hydrocarbyl or substituted hydrocarbyl provided that R¹⁷ does not contain any olefinic bonds; and

each R²⁷ is independently hydrocarbyl;
each X is a weakly coordinating anion;
provided that, when norbornene or substituted
norbornene is present, no other monomer is present.

200. The process as recited in claim 199 wherein both R^{27} are methyl.

201. The process as recited in claim 199 wherein said monomer is ethylene only.

202. The process as recited in claim 199 wherein said monomer is an α -olefin only.

203. The process as recited in claim 202 wherein said α -olefin is propylene.

one or more component selected from the group consisting of: a compound of the formula $CH_2=CH(CH_2)_mCO_2R^1$, wherein R^1 is hydrogen or, hydrocarbyl or substituted hydrocarbyl containing 1 to 10 carbon atoms, and m is 0 or an integer of 1 to 16; CO; and a vinyl ketone is also present.

205. The process as recited in claim 204 wherein m is 0, and \mathbb{R}^1 is hydrocarbyl or substituted hydrocarbyl.

15

20

25

30

35

206. The process as recited in claim 199 done in the presence of a solvent.

207. The process as recited in claim 199 wherein R^3 and R^4 are each independently hydrogen or methyl, and both R^2 and R^5 are 2,6-diisopropylphenyl.

208. The process as recited in claim 199 used to make a block polymer.

209. The process as recited in claim 199 wherein X is BAF, SbF₆, PF₆, or BF₄.

210. The process as recited in claim 207 wherein X is BAF or BF₄.

211. The process as recited in claim 210 wherein a monomer is ethylene or propylene.

212. The process as recited in claim 199 wherein the monomers are ethylene and propylene.

213. The process as recited in claim 199 wherein said monomers are part of a crude butenes stream.

 R^2 and R^5 are each independently hydrocarbyl, provided that the carbon atom bound to the imino nitrogen atom has at least two carbon atoms bound to it; and R^3 and R^4 are each independently hydrogen, hydrocarbyl, or R^3 and R^4 taken together are hydrocarbylene to form a carbocyclic ring, and each R^{17} is hydrocarbyl.

215. The process as recited in claim 199 wherein said olefin comprises cyclopentene.

216. A process for the polymerization of olefins, comprising, contacting, at a temperature of about - 100°C to about +200°C:


a first compound W, which is a neutral Lewis acid capable of abstracting either Q or S to form WQ or WS, provided that the anion formed is a weakly coordinating anion; or a cationic Lewis or Bronsted acid whose counterion is a weakly coordinating anion;

a second compound of the formula

10

20

25



and one or more monomers selected from the group consisting of ethylene, an olefin of the formula R¹⁷CH=CH₂ or R¹⁷CH=CHR¹⁷, cyclopentene, cyclobutene, substituted norbornene, and norbornene; wherein:

 R^{46} and R^{47} are each independently hydrocarbyl or substituted hydrocarby 1, provided that the carbon atom bound to the imino nitrogen atom has at least two carbon atoms bound to it;

R48 and R49 are each independently hydrogen, hydrocarbyl, or substituted hydrocarbyl;

each R31 is independently hydrocarbyl,

substituted hydrocarby , or hydrogen;

M is Ti, Zr, $\sqrt{}$, Cr, a rare earth metal, Co, Fe,

Sc, Ni, or Pd of oxidation state m; 15

y and z are positive integers;

y+z = m;

each R17 is independently hydrocarbyl or substituted hydrocarby provided that any olefinic bond in said olefin is separated from any other olefinic bond or aromatic fing by a quaternary carbon atom or at least two saturated carbon atoms;

Q is alk ψ l, hydride, chloride, iodide, or

bromide;

S is alkyl, hydride, chloride, iodide or bromide; and

provided that;

when norbornene or substituted norbornene is present, no other monomer is present;

when M is Pd a diene is not present; and 30

	except when M is Pd, when both Q and S are each
	independently chloride, bromide or iodide W is capable
	of transferring a hydride or alky group to M.
	217. The process as recited/in claim 216 wherein
5	eachR ³¹ is hydrogen.
	218. The process as recited in claim 216 wherein
	said monomer is ethylene only.
	219. The process as recited in claim 216 wherein
	said monomer is an α -olefin only.
10	220. The process as recited in claim 219 wherein
	said α -olefin is propylene.
	221. The process as recited in claim 216 done in
	the presence of a solvent. /
	222. The process as recited in claim 216 wherein
15	R ⁴⁸ and R ⁴⁹ are each independently hydrogen or methyl,
	both R46 and R47 are 2,6-disopropylphenyl, and T1 is
	methyl.
	223. The process as recited in claim 216 used to
•	make a block polymer. 224. The process as recited in claim 216 wherein M
20	/ N
	is Ni(II). 225. The process as recited in claim 216 wherein
	M is Pd(II).
	226. The process as recited in claim 225 wherein a
25	monomer is ethylene or propylene.
	227. The process as recited in claim 216 wherein:
	M is $Ti(IV)$, Q and S are chloride, and y and z are
	2;
	M is $Zr(IV)$, Q and S are chloride, and y and z are
30	2;
	M is $Co(II)$ Q and S are bromide, and y and z are
	1;
	M is $Fe(II)$, Q and S are chloride, and y and z are
	1;
35	M is Sc(IfI), Q and S are chloride, y is 1 and z
	is 2;

20

25

M is Ni(II), Q and S are bromide or chloride, and y and z are 1; M is Pd(II), Q and S are methyl, and y and z are 1;

M is Ni(I), Q is methyl, chloride, bromide, iodide or acetylacetonate, y is 1, and z is 0;

or

M is Ni(II), Q and S are methyl, and y and z are 1.

228. The process as recited in claim 216 wherein 10 the monomers are ethylene and propylene.

229. The process as recited in claim 216 wherein said monomers are part of a crude butenes stream.

230. The process as recited in claim 216 wherein:

R⁴⁶ and R⁴⁷ are each independently hydrocarbyl or substituted hydrocarbyl, provided that the carbon atom bound to the imino nitrogen atom has at least two carbon atoms bound to it;

R⁴⁸ and R⁴⁹ are each independently hydrogen, hydrocarbyl, or substituted hydrocarbyl;

each R³¹ is independently hydrocarbyl, substituted hydrocarbyl, or hydrogen; and

each R17 is hydrocarbyl.

231. The process as recited in claim 216 wherein said olefin comprises cyclopentene.

232. A compound of the formula

 $\begin{array}{c|c}
R^{3} & R^{2} \\
N & T^{1} \\
Pd & Z \\
R^{5} & X^{-} \\
\end{array}$ (III)

30 wherein:

R² and R⁵ are each independently hydrocarbyl or substituted hydrocarbyl, provided that the carbon atom bound to the imino nitrogen atom has at least two carbon atoms bound to it;

10.

20

25

30

 R^3 and R^4 are each independently hydrogen, hydrocarbyl, substituted hydrocarbyl, or R^3 and R^4 taken together are hydrocarbylene or substituted hydrocarbylene to form a carbocyclic ring;

T¹ is hydrogen, hydrocarbyl not containing olefinic or acetylenic bonds, R¹⁵C(=0) - or R¹⁵OC(=0) -;

Z is a neutral Lewis base wherein the donating atom is nitrogen, sulfur or oxygen, provided that if the donating atom is nitrogen then the pKa of the conjugate acid of that compound is less than about 6;

X is a weakly coordinating anion; and R¹⁵ is hydrocarbyl not containing olefinic or acetylenic bonds;

provided that when R³ and R⁴ taken together are

15 hydrocarbylene to form a carbocyclic ring Z is not an organic nitrile.

233. The compound as recited in claim 232 wherein T^1 is methyl, and Z is R^6 0 or R^7CN wherein each R^6 independently hydrogen or hydrocarbyl and R^7 is hydrocarbyl.

234. The compound as recited in claim 232 wherein R^3 and R^4 are each independently hydrogen or methyl or R^3 and R^4 taken together are 1,8-naphthylylene, and both R^2 and R^5 are 2,6-diffeopropylphenyl.

235. The compound as recited in claim 233 wherein R^3 and R^4 are each independently hydrogen or methyl, and both R^2 and R^5 are 2,6-diisopropylphenyl, and wherein X is BAF, SpF₆, PF₆, or BF₄.

236. The compound as recited in claim 232 wherein X is BAF, SbF₆, PF₆, or BF₄.

237. The compound as recited in claim 232 wherein R^2 and R^5 are each independently hydrocarbyl, provided that the carbon atom bound to the imino nitrogen atom has at least two carbon atoms bound to it; and R^3 and R^4 are each independently hydrogen, hydrocarbyl, or R^3 and R^4 taken together are hydrocarbylene to form a carbocyclic ring.

238. The compound as recited in claim 232 wherein each of R^2 , R^3 , R^4 , R^5 , T^1 , Z, and X are as follows:

R ²	R ³	R ⁴	R ⁵	/ T ¹	Z	X
				!		
o c i DwDh	Me	Me ·	2,6-i-PrPh	Me	OEt ₂	BAF
2,6-i-PrPh	н	н	2,6-i-PrPh	Me	OEt ₂	BAF
2,6-i-PrPh	. н	H	2,6-MePh	Me	OEt2	BAF
2,6-MePh	Me	Me	2,6-MePh	Me	OEt ₂	BAF
2,6-MePh	Me	Me	2,6-i-PrP#	Me	OEt2	SbF ₆
2,6-i-PrPh	Me	Me	2,6-i-PrPh	Me	OEt2	BF4
2,6-i-PrPh	Me	Me	2,6-i-P#Ph	Me	OEt2	PF ₆
2,6-i-PrPh	н	н	2,6-i-FrPh	Me	OEt2	SbF ₆
2,6-i-PrPh		Me	2,4,6-MePh	Me	OEt2	SbF ₆
2,4,6-MePh	Me	An	2,6-i-PrPh	Me	OEt2	SbF ₆
2,6-i-PrPh	An	Me	2,6-/i-PrPh	Me	NCMe .	SbF ₆
2,6-i-PrPh	Me	Me	Ph	Me	NCMe	SbF ₆
Ph	Me	Me	2,6-EtPh	Me	NCMe	BAF
2,6-EtPh	Me	Me	2,6-EtPh	Me	NCMe	SbF ₆
2,6-EtPh	Ме		2-t-BuPh	Me	NCMe	SbF6
2-t-BuPh	Me	Me	J-Np	Me	NCMe	SbF6
1-Np	Me-	Me	· Pr2CH	Me	NCMe	SbFe
Ph ₂ CH	H	H	2-PhPh	Me	NCMe	SbFe
2-PhPh	Me	Me	Ph	Me	NCMe	BAF
Ph	a	a/	Ph	Me	NCMe	sbF
Ph	Me	- 1.		Me	NCMe	BAF
Ph	Ph		Ph CY	Me	NCMe	SbF
Ph ₂ CH	н	- 1	Ph ₂ CH	Me	SMe ₂	SbF
Ph ₂ CH	H	/ H	Ph ₂ CH		-	

239. A compound of the formula

R3 N R4 N R51 wherein:

5

 g^{k_0} is substituted phenyl;

10

R⁵¹ is phenyl or substituted phenyl;
R³ and R⁴ are each independently hydrogen,
hydrocarbyl, substituted hydrocarbyl or R³ and R⁴ taken
together are hydrocarbylene or substituted
hydrocarbylene to form a ring;

and provided that groups in the 2 and 6 positions of R^{50} have a difference in $E_{\rm s}$ of about 0.15 or more.

240. The compound as recited in claim 239 wherein groups in the 2 and 6 of R^{51} have a difference in $E_{\rm s}$ of about 0.60 or more.

241. The compound as recited in claim 239 wherein the group in the 2 position of R^{50} is t-butyl and the group in 6 position of R^{50} is methyl or hydrogen.

242. The compound as recited in claim 241 wherein the group in the 2 position of R^{51} is t-butyl and the group in 6 position of R^{51} is methyl or hydrogen.

243. A compound of the formula

20 (XXXVI)

wherein:

R⁵² is substituted phenyl;

R⁵³ is pheryl of substituted phenyl;

 R^3 and R^4 are each independently hydrogen,

25 hydrocarbyl, substituted hydrocarbyl or R³ and R⁴ taken together are hydrocarbylene or substituted hydrocarbylene to form a ring;

Q is a kyl, hydride, chloride, bromide or

iodide;

S is alkyl, hydride, chloride, bromide or

iodide;

30

and provided that;

groups in the 2 and 6 positions of R^{52} have a difference in E_s of 0.15 or more; and

15

20

25

30

except when M is Pd, when both Q and S are each independently chloride, bromide or iodide W is capable of transferring a hydride or alkyl group to M.

244. The compound as redited in claim 243 wherein said difference is about 0.20 more.

245. The compound as recited in claim 243 wherein groups in the 2 and 6 of R^{51} have a difference in E_s of 0.15 or more.

246. The compound as recited in claim 243 wherein the group in the 2 position of R⁵² is i-propyl or t-butyl and the group in the 6 position of R⁵² is methyl or hydrogen.

247. The compound as recited in claim 246 wherein the group in the 2 position of R⁵³ is i-propyl or t-butyl and the group in 6 position of R⁵² is methyl or hydrogen.

248. A compound ϕ f the formula

R3 | R2 | T1 | Ni | Z | R5 | X | (III)

wherein:

 R^2 and R^2 are each independently hydrocarbyl or substituted hydrocarbyl, provided that the carbon atom bound to the imino nitrogen atom has at least two carbon atoms bound to it;

 R^3 and R^4 are each independently hydrogen, hydrocarbyl, substituted hydrocarbyl, or R^3 and R^4 taken together are hydrocarbylene or substituted hydrocarbylene to form a ring;

olefinic or acetylenic bonds, R¹⁵C(=0) - or R¹⁵OC(=0) -;
R¹⁵ is hydrocarbyl not containing an olefinic or acetylenic bond;

15

20

Z is a neutral Lewis base wherein the donating atom is nitrogen, sulfur or oxygen, provided that if the donating atom is nitrogen then the pKa of the conjugate acid of that compound is less than about 6;

X is a weakly coordinating anion.

249. The compound as recited in claim 248 wherein T^1 is methyl, Z is $R^6{}_2O$ wherein each R^6 is independently alkyl, and X is BAF, SbF₆, PF₆, or BF₄.

250. The compound as regited in claim 248 wherein R^3 and R^4 are each independently hydrogen or methyl, and both R^2 and R^5 are 2,6-diisopropylphenyl.

 R^3 and R^4 are each independently hydrogen or methyl, and both R^2 and R^5 are 2,6-diisopropylphenyl.

 R^2 and R^5 are each independently hydrocarbyl provided that the carbon atom bound to the imino nitrogen atom has at least two carbon atoms bound to it; and R^3 and R^4 are each independently hydrogen, hydrocarbyl, or R^3 and R^4 taken together are hydrocarbylene to form a ring.

253. A compound/of the formula

25 (IV)

30

wherein: R^2 and R^5 are each independently hydrocarbyl or substituted hydrocarbyl, provided that the carbon atom bound to the imino nitrogen atom has at least two carbon atoms bound to it;

 R^3 and R^4 are each independently hydrogen, hydrocarbyl, substituted hydrocarbyl, or R^3 and R^4

30

taken together are hydrocarbylene or substituted hydrocarbylene to form a ring;

M is Ni(II) or Pd(II);

each R16 is independently hydrogen or alkyl

5 containing 1 to 10 carbon at ϕ ms;

n is 1, 2, or 3;

x is a weakly coordinating anion; and

R⁸ is hydrocarbyl.

254. The compound as fecited in claim 253 wherein 10 R³ and R⁴ are each independently hydrogen or methyl, both R² and R⁵ are 2,6-diisopropylphenyl, M is Pd(II), and X is BAF, SbF₆, PF₆, or BF₄.

255. The compound as recited in claim 254 wherein each R^{16} is hydrogen and n is 3.

256. The compound as recited in claim 253 wherein M is Pd(II).

257. The compound as recited in claim 253 wherein each R^{16} is hydrogen and n is 3.

258. The compound as recited in claim 253 wherein R² and R⁵ are each independently hydrocarbyl, provided that the carbon atom bound to the imino nitrogen atom has at least two carbon atoms bound to it; and R³ and R⁴ are each independently hydrogen, hydrocarbyl, or R³ and R⁴ taken together are hydrocarbylene to form a ring.

259. A compound of the formula

R3

R4

R4

R5

(V)

wherein:

 R^2 and R^5 are each independently hydrocarbyl or substituted hydrocarbyl, provided that the carbon

10.

15

20

35

atom bound directly to the imin nitrogen atom has at least two carbon atoms bound to it;

 R^3 and R^4 are each independently hydrogen, hydrocarbyl, substituted hydrocarbyl, or R^3 and R^4 taken together are hydrocarbylene or substituted hydrocarbylene to form a ring;

E is halogen or -OR 18;

R¹⁸ is hydrocarbyl not containing olefinic or acetylenic bonds;

 T^1 is hydrogen, hydrocarbyl not containing olefinic or acetylenic bonds, $R^{15}C(=0)$ - or $R^{15}OC(=0)$ -; R^{15} is hydrocarbyl not containing olefinic or

acetylenic bonds; and

X is a weakly coordinating anion.

260. The compound as recited in claim 259 wherein R^2 and R^5 are each independently hydrocarbyl, provided that the carbon atom bound to the imino nitrogen atom has at least two carbon atoms bound to it; and R^3 and R^4 are each independently hydrogen, hydrocarbyl, or R^3 and R^4 taken together are hydrocarbylene to form a ring.

261. The compound as recited in claim 259 wherein T^1 is methyl, and E is chlorine.

262. The compound as recited in claim 261 wherein 25 R^3 and R^4 are each independently hydrogen or methyl, and both R^2 and R^5 are 2,6-diisopropylphenyl.

263. The compound as recited in claim 262 wherein X is BAF, SbF, PF_6 , or PF_4 .

264. A compound of the formula [$(\eta^4-1,5-$

30 COD) $PdT^{1}Z$] X, wherein:

 T^1 is hydrocarbyl not containing olefinic or acetylenic bonds;

X is a weakly coordinating anion;

cop is 1,5-cyclooctadiene;

 $Z/is R^{10}CN;$ and

 $R^{\downarrow 0}$ is hydrocarbyl not containing olefinic or acetylenic bonds.

265. The compound as recited in claim 264 wherein T^1 is methyl.

266. The compound as recited in claim 265 wherein Z is methyl and X is BAF, SbF, PF6, or BF4.

267. A compound of the formula

10 wherein:

5

15

20

25

30

M is Ni(II) of Pd(II);

R² and R⁵ are hydrocarbyl or substituted hydrocarbyl, provided that the carbon atom bound directly to the imino nitrogen atom has at least two carbon atoms bound to it;

R³ and R⁴ are each independently hydrogen, hydrocarbyl, substituted hydrocarbyl, or R³ and R⁴ taken together are hydrocarbylene or substituted hydrocarbylene to form a ring;

each R¹¹ is independently hydrogen, alkyl or - (CH₂)_mCO₂R¹;

T³ is hydrogen, hydrocarbyl not containing olefinic or acetylenic bonds, or -CH₂CH₂CH₂CO₂R⁸;

P is a divalent group containing one or more repeat units derived from the polymerization of one or more of ethylene, an olefin of the formula $R^{17}CH=CH_2$ or $R^{17}CH=CHR^{17}$, cyclobutene, cyclopentene, substituted norbornene, or norbornene and, when M is Pd(II), optionally one or more of: a compound of the formula $CH_2=CH(CH_2)_mCO_2R^1$, CO, or a vinyl ketone;

R⁸ is hydrocarbyl;

m is 0 or an integer from 1 to 16;

R¹/is hydrogen, or hydrocarbyl or substituted hydrocarbyl containing 1 to 10 carbon atoms;

15

20

and X is a weakly coordinating anion.

268. The compound as recited in claim 267 wherein R^1 is hydrocarbyl or substituted hydrocarbyl.

269. The compound as recited in claim 267 wherein

5 T^3 is hydrogen or alkyl.

270. The compound as refited in claim 267 wherein M is Pd(II).

271. The compound as recited in claim 269 wherein M is Pd(II).

 R^3 and R^4 are each independently hydrogen or methyl, and both R^2 and R^5 are 2,6-diisopropylphenyl.

273. The compound as recited in claim 271 wherein R^3 and R^4 are each independently hydrogen or methyl, and both R^2 and R^5 are 2/6-diisopropylphenyl.

 R^2 and R^5 are each independently hydrocarbyl, provided that the carbon atom bound to the imino nitrogen atom has at least two carbon atoms bound to it; and R^3 and R^4 are each independently hydrogen, hydrocarbyl, or R^3 and R^4 taken together are hydrocarbylene to form a ring.

275. A compound of the formula

 $\begin{array}{c|c}
R^{3} & R^{2} \\
N & T^{2} \\
N & X
\end{array}$ $\begin{array}{c|c}
R^{4} & N & X
\end{array}$ $\begin{array}{c|c}
R^{5} & X
\end{array}$

(VII)

25

30

wherein: R^2 and R^5 are each independently hydrocarbyl or substituted hydrocarbyl, provided that the carbon atom bound to the mino nitrogen atom has at least two carbon atoms bound to it;


 R^3 and R^4 are each independently hydrogen, hydrocarbyl, substituted hydrocarbyl, or R^3 and R^4

15

20

25

30



 T^2 is hydrogen, hydrocarbyl not containing olefinic or acetylenic bonds, hydrocarbyl substituted with keto or ester groups but not containing olefinic or acetylenic bonds, $R^{15}C(=0)$ - or $R^{15}OC(=0)$ -;

R¹⁵ is hydrocarbyl not containing ofefinic or acetylenic bonds; and

X is a weakly coordinating anion,

276. The compound as recited in claim 275 wherein T^2 is methyl.

277. The compound as recited in claim 276 wherein R^3 and R^4 are each independently hydrogen or methyl or R^3 and R^4 taken together are 1,8-naphthylylene, and both R^2 and R^5 are 2,6-diisopropylphenyl.

278. The compound as recited in claim 276 wherein X is BAF, SbF₆, PF₆, or BF₄.

279. The compound as recited in claim 275 wherein R^2 and R^5 are each independently hydrocarbyl, provided that the carbon atom bound to the imino nitrogen atom has at least two carbon atoms bound to it; and R^3 and R^4 are each independently hydrogen, hydrocarbyl, or R^3 and R^4 taken together are hydrocarbylene to form a ring.

280. A process for the production of polyolefins, comprising, contacting, at a temperature of about - 100°C to about +200°C, a compound of the formula

with one of more monomers selected from the group consisting of ethylene, an olefin of the formula

10

15

20

25

30

35



 $R^{17}CH=CH_2$ or $R^{17}CH=CHR^{17}$, cyclobutene, Eyclopentene, substituted norbornene, and norbornene,

wherein:

M is Ni(II) or Pd(II);

 R^2 and R^5 are hydrocarbyl ϕ r substituted hydrocarbyl, provided that the carbon atom bound directly to the imino nitrogen atom has at least two carbon atoms bound to it;

R³ and R⁴ are each independently hydrogen, hydrocarbyl, substituted hydrocarbyl, or R3 and R4 taken together are hydrocarbylene or substituted hydrocarbylene to form a ring;

each R11 is independently hydrogen, alkyl or -(CH₂)_mCO₂R¹;

T is hydrogen, hydrocarbyl not containing olefinic or acetylenic bonds, or -CH2CH2CH2CO2R8;

P is a divalent group containing one or more repeat units derived from the polymerization of one or monomers selected from the group consisting of ethylene, an olefin of the formula $R^{17}CH=CH_2$ or R¹⁷CH=CHR¹⁷, cyclopentene, cyclobutene, substituted norbornene, and norbornene, and, when M is Pd(II), optionally one or more of a compound of the formula $CH_2=CH(CH_2)_mCO_2R^1$, CO_1 , or vinyl ketone;

R⁸ is hydrocardyl;

each R17 is independently hydrocarbyl or substituted hydrodarbyl provided that any olefinic bond in said olefin is separated from any other olefinic bond or aromatic/ring by a quaternary carbon atom or at least two saturated carbon atoms;

R¹ is hydrogen, or hydrocarbyl or substituted hydrocarbyl containing 1 to 10 carbon atoms;

m is 0/or an integer of 1 to 16;

and X is a weakly coordinating anion;

provided that when norbornene or substituted norbornene is present no other monomer is present; when M is Pd a diene is not present; and

15

20

25

30

35



further provided that when M is Ni(II) R^{11} is not $-CO_2R^8$.

R² and R⁵ are each independently hydrocarbyl, provided that the carbon atom bound to the imino nitrogen atom has at least two carbon atoms bound to it; and R³ and R⁴ are each independently hydrogen, hydrocarbyl, or R³ and R⁴ taken together are hydrocarbylene to form a ring; and each R¹⁷ is hydrocarbyl.

282. The process as recited in claim 280 wherein T³ is methyl.

283. The process as recited in claim 282 wherein said monomer is ethylene only, and R¹¹ is hydrogen.

284. The process as recited in claim 282 wherein said monomer is an α -olefin only, and R^{11} is alkyl.

285. The process as recited in claim 284 wherein said α -olefin is propylene, and R^{11} is methyl.

286. The process as recited in claim 280 wherein M is Pd(II), and one or more comonomers selected from the group consisting of: a compound of the formula $CH_2=CH(CH_2)_mCO_2R^1$, wherein R^1 is hydrogen or, hydrocarbyl or substituted hydrocarbyl containing 1 to 10 carbon atoms, and m is 0 or an integer of 1 to 16; CO; and a vinyl ketone is also present.

287. The process as recited in claim 286 wherein m is 0, and R^1 is hydrocarbyl or substituted hydrocarbyl.

288. The process as recited in claim 287 wherein m is 0, and R^1 is hydrocarbyl or substituted hydrocarbyl.

289. The process as recited in claim 280 done in the presence of a solvent.

290. The process as recited in claim 280 done in the absence of a solvent.

291. The process as recited in claim 282 wherein R^3 and R^4 are each independently hydrogen or methyl or R^3 and R^4 taken together are 1,8-naphthylylene, and both R^2 and R^5 are 2,6-diisopropylphenyl.

292. The process as recited in claim 280 used to make a block polymer.

10.

15

293. The process as recited in claim 280 wherein X is BAF, SbF₆, PF₆, or BF₄.

The process as recited in claim 291 wherein 294. X is BAF, SbF₆, PF₆, or BF₄.

295. The process as recited/in claim 294 wherein a monomer is ethylene or propylene.

296. The process as recited in claim 280 wherein the monomers are ethylene and propylene.

297. The process as recited in claim 280 wherein said monomers are part of a crude butenes stream.

298. The process as recited in claim 280 wherein said monomers comprise cyclopentene.

299. A process for the production of polyolefins, comprising, contacting, at a temperature of about -100°C to about +200°C, a compound of the formula

$$R^{3}$$
 N
 $(Q)_{y}$
 H
 $C-R^{1}$
 R^{4}
 $H-C-R^{1}$
 R^{5}
 PT^{3}
 (XVI)
 $(X^{3})_{a}$

and one or more monomers selected from the group consisting of ethylene, an olefin of the formula 20 R¹⁷CH=CH₂ or R¹⁷CH=CHR¹, cyclobutene, cyclopentene, substituted norbornehe, and norbornene,

wherein:

M is Zr, Ti Sc, V, Cr, a rare earth metal, Fe,

Co, Ni or Pd of oxidation state m; 25

 R^2 and R^5 are each independently hydrocarbyl or substituted hydrocarbyl, provided that the carbon atom bound directly to the imino nitrogen atom has at least two carbon atoms bound to it;

 R^3 and R^4 are each independently hydrogen, hydrocarbyl, substituted hydrocarbyl, or R3 and R4 30 taken together are hydrocarbylene or substituted hydrocarbylene to form a ring;

15

20

25

35



each R11 is independently hydrogen or alkyl, or both of R11 taken together are hydrocarbylene to form a carbocyclic ring;

 T^3 is hydrogen, hydrocarbyl not containing olefinic or acetylenic bonds, or - H2CH2CH2CO2R8; Q is a 5 monoanion;

P is a divalent group containing one or more repeat units derived from the polymerization of one or monomers selected from the group consisting of ethylene, an olefin of the formula R17CH=CH2 or R¹⁷CH=CHR¹⁷, cyclopentene, cyclobutene, substituted norbornene, and norbornene, and when M is Pd(II), optionally one or more of: a compound of the formula CH₂=CH(CH₂)_mCO₂R¹, CO, or a viny ketone;

R⁸ is hydrocarbyl; a is 1 or 2;

y + a + 1 = m;each R17 is independently hydrocarbyl or substituted hydrocarbyl provided that any olefinic bond in said olefin is separated from any other olefinic bond or aromatic ring by a quaternary carbon atom or at least two saturated carbon atoms;

R¹ is hydrogen, or hydrocarbyl or substituted hydrocarbyl containing 1 to 10 carbon atoms;

m is 0 or an integer of 1 to 16;

and X is a weakly coordinating anion;

provided that, when norbornene or substituted norbornene is present, ho other monomer is present;

when M is Pd a diene in not present; and

further provided that, when M is Ni(II), T^3 is not -30 CH₂CH₂CH₂CO₂R⁸.

300. The process as recited in claim 299 wherein $\ensuremath{R^2}$ and $\ensuremath{R^5}$ are each independently hydrocarbyl, provided that the carbon atom/bound to the imino nitrogen atom has at least two carbon atoms bound to it; and R3 and R^4 are each independently hydrogen, hydrocarbyl, or R^3 and R4 taken together are hydrocarbylene to form a ring; and each R^{17} is hydrocarbyl.

15

20

25

30



301. The process as recited in claim 299 wherein T^3 is methyl.

302. The process as recited in claim 301 wherein said monomer is ethylene only, and R^{11} is hydrogen.

303. The process as recited/in claim 301 wherein said monomer is an α -olefin only, and R^{11} is alkyl.

304. The process as recited in claim 303 wherein said α -olefin is propylene, and each R^{11} is methyl or hydrogen.

305. The process as recited in claim 299 wherein M is Pd(II), and one or more comonomer selected from the group consisting of: a compound of the formula $CH_2=CH(CH_2)_mCO_2R^1$, wherein R^1 is hydrogen or, hydrocarbyl or substituted hydrocarbyl containing 1 to 10 carbon atoms, and m is 0 or an integer of 1 to 16; CO; and a vinyl ketone is also present.

306. The process as recited in claim 305 wherein m is 0, and R^1 is hydrocarbyl or substituted hydrocarbyl.

307. The process as recited in claim 299 done in the presence of a solvent.

308. The process as recited in claim 299 done in the absence of a solvent.

 R^3 and R^4 are each independently hydrogen or methyl, and both R^2 and R^5 are $\frac{1}{2}$, $\frac{1}{6}$ diisopropylphenyl.

310. The process as recited in claim 299 used to make a block polymer.


311. The process as recited in claim 299 wherein X is BAF, SbF₆, PF₆, or BF₄.

312. The process as recited in claim 309 wherein X is BAF, SbF₆, PF₆, or BF₄.

313. The process as recited in claim 312 wherein a monomer is ethylene or propylene.

314. The process as recited in claim 299 wherein the monomers are ethylene and propylene.

315. The process as recited in claim 299 wherein said monomers are part of a crude butenes stream.



317. A compound of the formula

$$R^{3}$$
 N
 $(C)_{y}$
 H
 $C-R^{1}$
 N
 $H-C-R^{1}$
 PT^{3}
 (XVI)
 $(X)_{a}$

5

10

20

25

wherein:

M is Zr, Ti, Sc, V, Cr, a rare earth metal, Fe, Co, Ni or Pd of oxidation state m;

R² and R⁵ are each independently hydrocarbyl or substituted hydrocarbyl, provided that the carbon atom bound directly to the imino nitrogen atom has at least two carbon atoms bound to it;

R³ and R⁴ are each independently hydrogen, 15 hydrocarbyl, substituted hydrocarbyl, or R³ and R⁴ taken together are hydrocarbylene or substituted hydrocarbylene to form a ring;

each R¹¹ is independently hydrogen, or alkyl, or both of R¹¹ taken together are hydrocarbylene to form a carbocyclic ring;

 T^3 is hydrogen, hydrocarbyl not containing olefinic or acetylenic bonds, or $-CH_2CH_2CH_2CO_2R^8$;

P is a divalent group containing one or more repeat units derived from the polymerization of one or monomers selected from the group consisting of ethylene, an olefin of the formula R¹⁷CH=CH₂ or R¹⁷CH=CHR¹⁷, cyclopentene, cyclobutene, substituted norbornene, and norbornene, and optionally, when M is Pd(II), one or more of: a compound of the formula CH₂=CH(CH₂)_mCO₂R¹, CO, or a vinyl ketone;

Q is a monovalent anion; R⁸ is hydrocarbyl; a is 1 or 2;

15

20

30



v + a + 1 = m;

each R17 is independently hydrocarbyl or substituted hydrocarbyl provided that any olefinic bond in said olefin is separated from any other olefinic bond or aromatic ring by a quaternary carbon atom or at least two saturated carbon atoms;

R1 is hydrogen, or hydrocarbyl or substituted hydrocarbyl containing 1 td 10 carbon atoms;

m is 0 or an integer of 1 to 16; and and X is a weakly coordinating anion;

and provided that when M is Pd a diene is not present;.

318. The compound as recited in claim 317 wherein R1 is hydrocarbyl or substituted hydrocarbyl.

319. The compound as recited in claim 317 wherein T³ is hydrogen or alkyl

320. The compound as recited in claim 317 wherein R^2 and R^5 are each independently hydrocarbyl, provided that the carbon atom bound to the imino nitrogen atom has at least two carbon atoms bound to it; and \mathbb{R}^3 and R4 are each independently hydrogen, hydrocarbyl, or R3 and R4 taken together are hydrocarbylene to form a ring; and each R^{17} is hydrocarbyl.

321. The compound as recited in claim 317 wherein

M is Pd(II). 25

322. The compound as recited in claim 319 wherein M is Pd(II).

323. The compound as recited in claim 317 wherein R^3 and R^4 are each/independently hydrogen or methyl, and both R^2 and R^5 are 2,6-diisopropylphenyl.

324. The compound as recited in claim 317 wherein both of R¹¹ taken together form a five-membered carbocyclic ring

325. The compound as recited in claim 317 wherein both of R11 taken together are hydrocarbylene to form a 35 carbocyclic ring.

326. A process, comprising, contacting, at a temperature of about -40°C to about +60°C, a compound



of the formula $[(\eta^4-1,5-COD)PdT^1Z]X^-$ and a diimine of the formula

5 (VIII)

to produce a compound of the formula

10

15

20

25

wherein:

 T^1 is hydrogen, hydrocarbyl not containing olefinic or acetylenic bonds, $R^{15}C(=0)$ - or $R^{15}OC(=0)$ -;

X is a weakl coordinating anion;

COD is 1,5-dyclooctadiene;

Z is R¹⁰CN;

R¹⁰ is hydrocarbyl not containing olefinic or acetylenic bonds;

R¹⁵ is hydrocarbyl not containing olefinic or acetylenic bonds;

 R^2 and R^5 are each independently hydrocarbyl or substituted hydrocarbyl, provided that the carbon atom bound to the imino nitrogen atom has at least two carbon atoms bound to it; and

 R^3 and R^4 are each independently hydrogen, hydrocarbyl, substituted hydrocarbyl, or R^3 and R^4 taken together are hydrocarbylene or substituted hydrocarbylene to form a ring.



327. The process as recited in claim 326 wherein R^{10} is alkyl, and T^{1} is methyl.

328. The process as recited in claim 326 carried out in a solvent of the formula R^{10} CN, wherein R^{10} is hydrocarbyl not containing olefinic or acetylenic bonds.

329. The process as recited in claim 327 wherein R^3 and R^4 are each independently hydrogen or methyl, and both R^2 and R^5 are 2,6-diisopropylphenyl.

330. The process as recited in claim 326 wherein X is BAF, SbF₆, PF₆, or BF₄.

331. The process as recited in claim 326 wherein R^2 and R^5 are each independently hydrocarbyl, provided that the carbon atom bound to the imino nitrogen atom has at least two carbon atoms bound to it; and R^3 and R^4 are each independently hydrogen, hydrocarbyl, or R^3 and R^4 taken together are hydrocarbylene to form a ring.

332. An ethylene homopolymer with a density of

20 0.86 g/ml or less.

333. The ethylene homopolymer as recited in claim
332 wherein said density is about 0.85 or less.

. 334. A compound of the formula

25

10.

15

(XIV)

wherein:

30 R² and R⁵ are each independently hydrocarbyl or substituted hydrocarbyl, provided that the carbon atom bound to the imino nitrogen atom has at least two carbon atoms bound to it;

25

30



R³ and R⁴ are each independently hydrogen, hydrocarbyl, substituted hydrocarbyl, or R³ and R⁴ taken together are hydrocarbylene or substituted hydrocarbylene to form a ring;

each R²⁷ is hydrocarbyl; and

each X is a weakly coordinating anion.

R² and R⁵ are each independently hydrocarbyl, provided that the carbon atom bound to the imino nitrogen atom has at least two carbon atoms bound to it; and R³ and R⁴ are each independently hydrogen, hydrocarbyl, or R³ and R⁴ taken together are hydrocarbylene to form a ring.

336. The compound as recited in claim 334 wherein both of R^{27} are methyl.

337. The compound as recited in claim 334 wherein R^3 and R^4 are each independently hydrogen or methyl or R^3 and R^4 taken together are 1,8-naphthylylene, and both R^2 and R^5 are 2,6 diisopropylphenyl.

338. The compound as recited in claim 334 wherein X is BAF, SbF₆, PF₆, or BF₄.

339. A compound of the formula

M is Mi(II) or Pd(II);

 R^2 and R^5 are each independently hydrocarbyl or substituted hydrocarbyl, provided that the carbon atom bound directly to the imino nitrogen atom has at least two carbon atoms bound to it;

 R^3 and R^4 are each independently hydrogen, hydrocarbyl, substituted hydrocarbyl, or R3 and R4 taken together are hydrocarbylene or substituted hydrocarbylene to form a fing; each R14 is independently hydrogen, alkyl 5 - $(CH_2)_mCO_2R^1$; R¹ is hydrogen, or hydrocarbyl or substitu hydrocarbyl containing/1 to 10 carbon atoms; T^4 is alkyl, $-\sqrt{R^{60}C(0)OR^8}$, $R^{15}(C=0)$ - or $R^{15}O($ R¹⁵ is hydro¢arbyl not containing olefini 10 acetylenic bonds; R⁶⁰ is alkylene not containing olefinic c acetylenic bonds; R⁸ is hydrocarbyl;; and X is a weakly coordinating anion; 15 and provided that when R^{14} is $-(CH_2)_mCO_2R^3$ is not alkyl, M is Pd(II). 340. The compound as recited in claim 339 R^2 and R^5 are each independently hydrocarbyl, pr that the carbon atom bound to the imino nitroge 20 has at least two carbon atoms bound to it; and R4 are each/independently hydrogen, hydrocarbyl and R4 taken together are hydrocarbylene to for 341./The compound as recited in claim 339 ring. 25 T4 is methyl and M is Pd(II). 342. The compound as recited in claim 339 each R^{14}/is independently hydrogen or $-(CH_2)_mC^{(1)}$ is Pd(II). 30

343. A homopolypropylene with a glass tratemperature of -30°C or less, provided that sa homopolypropylene has at least 50 branches per methylene groups.

344. The homopolypropylene as recited in wherein said glass transition temperature is 35°C or less.

35

byl or n atom least

in

b

m d

 R^3

ein m

einn

Or 5

rein

T.

25





345. A homopolymer of cyclopentene having a degree of polymerization of about 30 or more and an end of melting point of about 100°C to about/320°C, provided that said homopolymer has less than \$ mole percent of enchained linear olefin containing pentylene units.

346. The homopolymer as recited in claim 345 wherein at least 90 percent of repeat units are 1,3cyclopentylene repeat units.

347. The homopolymer as recited in claim 345 wherein at least 90 percent of repeat units are cis-10 1,3-cyclopentylene repeat units.

348. The homopolymer as recited in claim 345 wherein an X-ray powder diffraction pattern thereof has reflections at approximately 17.3°, 19.3°, 24.2°, and 40.7° 2θ .

349. A homopolymer of cyclopentene that has an Xray diffraction pattern with reflections at approximately 17.3°, 19.3%, 24.2°, and 40.7° 2 θ .

350. The homopolymer as recited in claim 349 which has a monoclinic unit cell of the approximate dimensions: a=0.561 nm;/ b=0.607 nm; c=7.37 nm; and20 $q=123.2^{\circ}$.

351. The homopolymer as recited in claim 349 wherein at least 90 percent of repeat units are 1,3cyclopentylene repeat units.

352. The homop ϕ lymer as recited in claim 351 wherein at least 90 percent of repeat units are cis-1,3-cyclopentylene/repeat units.

353. A homop ϕ lymer of cyclopentene wherein at least 90 mole percent of enchained cyclopentylene units are 1,3-cyclopen tylene units, and said homopolymer has 30 an average degree of polymerization of 30 more.

354. A homopolymer of cyclopentene wherein at least 90 mole percent of enchained cyclopentylene units are cis-1,3-cyclopentylene, and said homopolymer has an average degree of polymerization of about 10 or more. 35

25

30

00

355. A copolymer of cyclopentene and ethylene wherein at least 75 mole percent of enchained cyclopentylene units are 1,3 cyclopentylene units.

356. The copolymer as recited in claim 355 whe at least 50 mole percent of the repeat units are derived from cyclopentene

357. The copolymer as recited in claim 355 who there are at least 20 branches per 1000 methyle=ne carbon atoms.

358. A copolymer of cyclopentene and ethylene wherein there are at least 20 branches per 100□ methylene carbon atoms.

359. The copolymer as recited in claim 358 wh at least 50 mole percent of the repeat units are derived from ethylene.

360. A copolymer of cyclopentene and ethy leng wherein at least 50 mole percent of the repeat unit are derived from cyclopentene.

361. A copolymer comprising repeat units of cyclopentene and an α -olefin.

362. The copolimer as recited in claim 361 w repeat units derived from ethylene are also prese

363. The copolymer as recited in claim 361 w said α -olefin is a linear α -olefin.

364. The copolymer as recited in claim 3 61 v at least 90 mole percent of repeat units derived cyclopentene are 1,3-cyclopentylene units.

at least 90 mole percent of repeat units derived cyclopentene are cis-1,3-cyclopentylene units.

366. A fiber made from the polymer of cLaim 349, 353, 354, 355, 356, 357, 358, 360 or 361.

367 A polymerization process, comprising, contacting an olefin of the formula R¹⁷CH=CH₂ or R¹⁷CH=CHR¹⁷, each R¹⁷ is independently hydrogem, hydrocarbyl, or substituted hydrocarbyl provided any olefinic bond in said olefin is separated for other olefinic bond or aromatic ring by a quate:

nits has

nits is an

10

15

20

25

30

35



carbon atom or at least two saturated carbon atoms with a catalyst, wherein said catalyst:

contains a nickel or palladium atom in a positive oxidation state;

contains a neutral bidentate ligand coordinated to said nickel or palladium atom, and wherein coordination to said nickel or palladium atom is through two nitrogen atoms or a nitrogen atom and a phosphorous atom; and

said neutral bidentate ligand, has an Ethylene Exchange Rate of less than 20,000 L-mol⁻¹s⁻¹ when said catalyst contains a palladium atom, and less than 50,000 L-mol⁻¹s⁻¹ when said catalyst contains a nickel atom;

and provided that when M is Pd a diene is not present.

368. The polymerization process as recited in claim 367 wherein said Ethylene Exchange Rate is less than 10,000 L-mol⁻¹s⁻¹ when said catalyst contains a palladium atom, and less than 25,000 L-mol⁻¹s⁻¹ when said catalyst contains a nickel atom.

369. The process as recited in claim 367 wherein said bidentate ligand is coordinated to said nickel or palladium atom through two nitrogen atoms.

370. The process as recited in claim 369 wherein said ligand is an α diimine.

371. The process as recited in claim 367 wherein said olefin has the formula $R^{17}CH=CH_2$, wherein R^{17} is hydrogen or n-alkyl.

372. A process for the polymerization of olefins, comprising, contacting, at a temperature of about $+200^{\circ}\text{C}$:

a first compound which is a source of a relatively noncoordinating monoanion;


a sedond compound of the formula

15

20

25

30



and one or more monomers selected from the group consisting of ethylene, an olefin of the formula R¹⁷CH=CH₂ or R¹⁷CH=CHR¹⁷, cyclobutene, cyclopentene, substituted norbornene, or norbornene;

wherein

 R^2 and R^5 are each independently hydrocarbyl or substituted hydrocarbyl, provided that the carbon atom bound to the imino nitrogen atom has at least two carbon atoms bound to it;

 R^3 and R^4 are each independently hydrogen, hydrocarbyl, substituted hydrocarbyl, or R^3 and R^4 taken together are hydrocarbylene or substituted hydrocarbylene td form a ring;

each R17 is independently hydrocarbyl or substituted hydrocarbyl provided that R17 does not contain any olefinic bords;

T is hydrogen, hydrocarbyl not containing olefinic or acetyleric bonds, $R^{15}C(=0)$ - or $R^{15}OC(=0)$ -; S is chloride, iodide, or bromide; and

provided that, when norbornene or substituted norbornene is present no_other monomer is present.

373. The process as recited in claim 372 wherein R^2 and R^5 are each independently hydrocarbyl, provided that the carbon atom bound to the imino nitrogen atom has at least two carbon\atoms bound to it; and R³ and R^4 are each independently hydrogen, hydrocarbyl, or R^3 and R4 taken together are hydrocarbylene to form a ring; and each R17 is saturated hydrocarbyl.

374. The process as recited in claim 372 wherein said source is an alkali metal salt of said anion.

25

30

35

20;



375. The process as recited in claim 372 wherein T^1 is methyl.

376. The process as recited in claim 372 wherein said monomer is ethylene only, and \mathbb{R}^{11} is hydrogen.

377. The process as recited in claim 372 wherein one or more comonomer selected from the group consisting of: a compound of the formula $CH_2=CH(CH_2)_mCO_2R^1$, wherein R^1 is hydrogen or, hydrocarbyl or substituted hydrocarbyl containing 1 to 10 carbon atoms, and m is 0 or an integer of 1 to 16; CO; and a vinyl ketone is also present.

378. The process as recited in claim 372 done in the presence of a solvent.

379. The process as recited in claim 368 used to make a block polymer.

380. The process as recited in claim 368 wherein said monoanion is BAF, SbF_6 , PF_6 , or BF_4 .

381. The process as recited in claim 374 wherein said monoanion is BAF, $\$bF_6$, PF_6 , or BF_4 .

382. The process as recited in claim 377 wherein a monomer is ethylene or propylene.

383. The process as recited in claim 372 wherein the monomers are ethylene and propylene.

384. A polyolefin, comprising, a polymer made by polymerizing one or more monomers of the formula $H_2C=CH(CH_2)_eG$ by contacting said monomers with a transition metal containing coordination polymerization catalyst, wherein:

each G is independently hydrogen or -CO₂R¹; each e is independently 0 or an integer of 1 to

each R¹ is independently hydrogen, hydrocarbyl or substituted hydrocarbyl;

and provided that:

said polymer has at least 50 branches per 1000 methylene groups;

in at least 50 mole percent of said monomers G is hydrogen;

473

15

20

25

except when no branches should be theoretically present, the number of branches per 1000 methylene groups is 90% or less than the number of theoretical branches per 1000 methylene groups, or the number of branches per 1000 methylene groups is 110% or more of theoretical branches per 1000 methylene groups; and

when there should be no branches theoretically present, said polyolefin has 50 or more branches per 1000 methylene groups;

and provided that said/polyolefin has at least two branches of different lengths containing less than 6 carbon atoms each.

wherein except when no branches should be theoretically present the number of branches per 1000 methylene groups is 80% or less than the number of theoretical branches per 1000 methylene groups, or the number of branches per 1000 methylene groups is 120% or more of theoretical branches per 1000 methylene groups is 120% or more of theoretical branches per 1000 methylene groups; and

when there should be no branches theoretically present, said polyolefin has 75 or more branches per 1000 methylene groups.

386. A polyolefin comprising, a polymer made by polymerizing one or more monomers of the formula $H_2C=CH(CH_2)_eG$ by contacting said monomers with a transition metal containing coordination polymerization catalyst, wherein:

each G is independently hydrogen or -CO₂R¹; each e is independently 0 or an integer of 1 to

30 20;

 \mathbb{R}^1 is independently hydrogen, hydrocarbyl or substituted hydrocarbyl;

and provided that:

said polymer has at least 50 branches per 1000

35 methylene groups;

in at least 50 mole percent of said monomers G is hydrogen;

10

15

20

25

35



said polymer has at least 50 branches of the formula $-(CH_2)_f G$ per 1000 methylene groups, wherein when G is the same as in a monomer and e $\neq f$, and/or for any single monomer of the formula $H_2C=CH(CH_2)_e G$ there are less than 90% of the number of theoretical branches per 1000 methylene groups, or more than 110% of the theoretical branches per 1000 methylene groups of the formula $-(CH_2)_f G$ and f=e, and wherein f is 0 or an integer of 1 or more;

and provided that said polyolefin has at least two branches of different lengths containing less than 6 carbon atoms each.

387. The polyolefin as recited in claim 386 wherein when G is the same as in a monomer and $e \neq f$, and/or for any single monomer of the formula $H_2C=CH(CH_2)_eG$ there are less than 80% of the number of theoretical branches per 1000 methylene groups, or more than 120% of the theoretical branches per 1000 methylene groups of the formula $-(CH_2)_fG$ and f=e.

388. A tackifier for an adhesive comprising the polymer of claim 1, 2, 3, 5, 6 or 7.

389. An oil additive for smoke suppression in twostroke gasoline engines comprising the polymer of claim 1, 2, 3, 4, 5, 6, or

390. A base resin for a hot melt adhesive, a pressure sensitive adhesive or a solvent applied adhesive comprising the polymer of claim 1, 2, 3, 4, 5, 6 or 7.

391. A viscosity modifier for lubricating oils
30 comprising the polymer of claim 1, 2, 3, 4, 5, 6 or 7.

392. A coating or penetrant comprising the polymer of claim 1, 2, 4, 5, 6 or 7.

393. A base polymer for caulking comprising the polymer of claim 1, 2, 3, 4, 5, 6 or 7.

394 The polymer of claim 1, 2, 4, 5, 6 or 7 which is grafted so it contains functional groups.

39\$. A toughener for a thermoplastic or a thermoset comprising the polymer of claim 14.

475

10

25



396. A modifier for asphalt comprising the polymer of claim 1, 3, 4, 6, 7, 332 or 343.

397. The polymer of claim 1, 3, 4, 6, 7, 332 or 343 which is chlorinated or chlorosulfonated.

398. The polymer of claim 17/which is elastomeric.

399. A wire insulation or jacketing comprising the polymer of claim 1, 3, 4, 6, 7, 332 or 343.

400. A toughener for polyotefins comprising the polymer of claim 1, 3, 4, 6, 7, 332 or 343.

401. A base for a synthetic lubricant comprising the polymer of claim 1, 4, 6, 7, 332 or 343.

402. A drip suppressant for synthetic polymers comprising the polymer of claim 1, 3, 4, 6, 7, 332 or 343.

15 403. A blown or cast film, or a sheet comprising the polymer of claim 1, 3, $\frac{1}{4}$, 6, 7, 332 or 343.

404. An additive for wax candles for smoke suppression or drip control comprising the polymer of claim 1, 4, 6, 7, 332 or 343.

20 405. A base resin for carpet backing comprising the polymer of claim 1, 3, 4, 6, 7, 332 or 343.

406. A capliner resin comprising the polymer of claim 1, 3, 4, 6, 7, 332 Ar 343.

407. A thermal transfer imaging resin comprising the polymer of claim 1, 1, 6, 7, 332 or 343.

408. An extrusion or coextrusion onto a plastic, metal, textile or paper web comprising the polymer of claim 1, 3, 4, 6, 7, 332 or 343.

409. A laminating adhesive for glass comprising the polymer of claim 1, 3, 4, 6, 7, 332 or 343.

410. A foamed object comprising the polymer of claim 1, 3, 4, 6 7, 332 or 343.


411. A powder used to coat an object comprising the polymer of claim 1, 3, 4, 6, 7, 332 or 343.

35 412. A hose comprising the polymer of claim 1, 3, 4, 6, 7, 332 of 343.

47.6

25

35



343.
414. A nonwoven fabric comprising the polymer of claim 1, 3, 4, 6, 7, 332 or 343.

415. A roofing membrane comprising the polymer of claim 1, 3, 4, 6, 7, 332 or 343.

416. A reactive diluent for an automotive finish comprising the polymer of claim 7, 8, 9, 10, 11 or 12.

10 417. An ionomer comprising the polymer of claim 7, 8, 9, 10, 11 or 12.

418. A molding resin comprising the ionomer of claim 417.

419. A core for the initiation of condensation polymerizations yielding a grafted branched polymer, comprising the polymer of claim 7, 8, 9, 10, 11, or 12.

of claim 3, 6 or 7.

421. A toughener for a thermoplastic or thermoset 20 comprising the polymer of claim 1, 3, 4, 6, 7, 332 or 343.

422. An internal plasticizer for polymers

comprising the polymer of claim 1, 3, 4, 6, 7, 332 or

343.

423. An adhesive for adhering a polymer comprising the polymer of claim 3, 6, 7, 332 or 343.

424. A curing agent for a polymer containing complimentary functional groups comprising the polymer of claim 3, 6 or 7.

30 425. An additive to thermoplastic polymers to improve the adhesion of paint thereto comprising the polymer of claim 3, 6 or 7.

426. A polymer blend comprising the polymer of claim 1, 3, 4, 6, 7, 332 or 343 and at least one other polymer.


427. A polymer of one or more alpha-olefins of the formula $CH_2=CH(CH_2)$ aH wherein a is an integer of 2 or more, which contains the structure

15

20

25

35



wherein R^{35} is an alkyl group and R^{36} is an alkyl group containing two or more carbon atoms, and provided that R^{35} is methyl in at least about 2 mole percent of the total amount of (XXV) in said polymer.

428. The polymer as recited in claim 427 wherein a structure in which R³⁵ is methyl is about 5 mole percent or more of the total amount of (XXV) in said polymer.

429. The polymer as recited in claim 427 wherein a structure in which R³⁵ is methyl is about 50 mole percent or more of the total amount of (XXV) in said polymer.

430. A polymer of one or more alpha-olefins of the formula $CH_2=CH(CH_2)$ all wherein a is an integer of 2 or more, wherein said polymer contains methyl branches and said methyl branches are about 25 to about 75 mole percent of the total branches in said polymer.

431. The polymer as recited in claim 430 which contains branches of the formula $-(CH_2)_aH$.

432. The polymer as recited in claim 430 which contains branches of the formula $-(CH_2)_{n}H$ wherein n is an integer of 6 or greater.

433. The polymer as recited in claim 431 which contains the structure

 CH_3 $-CH_2-CH-(CH_2)_aH$ (XXVI)

and wherein (XXVI) is present in an amount of 0.5 branches of (XXVI) or more per 1000 methylene atoms greater than can be accounted for by end groups.


434. A polyethylene dontaining the structure (XXVII) in an amount greater than can be accounted for by end groups.

10

15

25

30



435. The polyethylene as recited in claim 434 which contains about 2 or more of (XXVII) per 1000 methylene groups in said polymer.

436. A polypropylene containing one or both of the structures (XXVIII) and (XXIX), provided that:

(XXIX), if present is present in an amount greater than of equal to 0.5 of (XXIX) per 1000 methylene groups greater than can be accounted for by end groups;

or the polymer contains at least 0.5 or more of (XXVIII) per 1000 methylene groups, if (XXVIII) is present.


437. The polypropylene as recited in claim 436 which contains about 1/5 or mode groups of structure 20 (XXVIII) per 1000 methylene groups in said polypropylene.

438. The polypropylene as recited in claim 436 which contains about 15 or more groups of structure (XXIX) per 1000 methylene groups in said polypropylene.

439. A process for the formation of linear α olefins, comprising, contacting, at a temperature of about -100°C to about +20 \dot{q} °C:

ethylene;

a first compound W, which is a neutral Lewis acid capable of abstracting X^{-} the form WX^{-} , provided that the anion formed is a weakl γ coordinating anion, or a



a second compound of the formula

5

10

15

20

25

30

(XXXI)

wherein:

R² and R⁵ are each independently hydrocarbyl or substituted hydrocarbyl;

R³ and R⁴ are each independently hydrogen, substituted hydrocarbyl, hydrocarbyl, or \mathbb{R}^3 and \mathbb{R}^4 taken together are hydrocarbylene or substituted hydrocarbylene to form a ring; and

Q and S are each independently chlorine, bromine, iodine or alkyl; and

wherein an α -plefin containing 4 to 40 carbon atoms is produced.

440. The process as recited in claim 439 wherein said linear α -olefin/has the formula $H_2C=CHR^1$, wherein R^1 is n-alkyl containing 2 to 30 carbon atoms.

441. The process as recited in claim 439 wherein R² and R⁵ are phenyl

442. The process as recited in claim 439 wherein R^3 and R^4 are hydrogen, methyl or 1,8-naphthylylene.

443. The process as recited in claim 440 wherein

 R^3 and R^4 are hydrogen, methyl or 1,8-naphthylylene.

444. The process as recited in claim 439 wherein said second compound is an alkyl aluminum compound.


445. The process as recited in claim 444 wherein said alkyl aluminum compound is R3Al, R2AlCl, RAlCl2, R⁹₃Al₂Cl₃, or R⁹AlO, wherein R⁹ is alkyl containing 1 to 25 carbon atoms.

446. The process as recited in claim 445 wherein R⁹ contains 1 to 4 carbon atoms.

10

15

20



said second compound is R⁹3Al, R⁹2AlCl, R⁹AlCl₂, or R9AlO, R93Al2Cl3, wherein R9 is alkyl containing 1 to 25 carbon atoms.

448. The process as recited in claim 439 carried out at a temperature of about 25°C to about 100°C.

449. The process as recited in claim 439 wherein a partial pressure of said ethylene is about atmospheric

pressure to about 275 MPa.

450. The process as recited in claim 439 wherein R^2 and R^5 are each independently hydrocarbyl, provided that the carbon atom bound to the imino nitrogen atom has at least two carbon atoms bound to it; and R3 and R4 are each independent by hydrogen, hydrocarbyl, or R3 and R4 taken together are hydrocarbylene to form a ring.

451. A process for the formation of linear α olefins, comprising, contacting, at a temperature of

about -100°C to about +200°C:

ethylene and/a compound of the formula

X-(III)

or

25

(XXXIV)

wherein:

 R^2 and R^5 are each independently hydrocarbyl or substituted hydrocarbyl;

 R^3 and R^4 are each independently hydrogen, substituted hydrocarbyl, hydrocarbyl, or R^3 and R^4 taken together are hydrocarbylene or substituted. hydrocarbylene to form a ring;

 T^1 is hydrogen or n-alkyl containing up to 38 carbon atoms;

Z is a neutral Lewis base wherein the donating atom is nitrogen, sulfur, or oxygen, provided that if the donating atom is nitrogen then the pKa of the conjugate acid of that compound (measured in water) is less than about 6;

U is n-alkyl containing up to 38 carbon atoms;

15 and

20

10

X is a noncoordinating anion;

and wherein an α -ofefin containing 4 to 40 carbon atoms is produced.

452. A process for the production of polyolefins, comprising, contacting, at a temperature of about 0°C to about +200°C, a compound of the formula

XXXVII

and one or more monomers selected from the group consisting of ethylene, an olefin of the formula 25 $R^{17}CH=CH_2$ or $R^{17}CH=CHR^{17}$, cyclobutene, cyclopentene, substituted norbornene, and norbornene,

whereih:


M is Ni(II) or Pd(II); 30

A is a π -allyl or π -benzyl group;

 R^2 and R^5 are each independently hydrocarbyl or substituted hydrocarbyl, provided that the carbon atom

25

30



bound directly to the imino nitrogen atom has at least two carbon atoms bound to it;

 R^3 and R^4 are each independently hydrogen, hydrocarbyl, substituted hydrocarbyl or R^3 and R^4 taken together are hydrocarbylene or substituted hydrocarbylene to form a ring;

each R¹⁷ is independently hydrocarbyl or substituted hydrocarbyl provided that any olefinic bond in said olefin is separated from any other olefinic bond or aromatic ring by a quaternary carbon atom or at least two saturated carbon atoms; R¹ is hydrogen, or hydrocarbyl or substituted hydrocarbyl containing 1 to 10 carbon atoms;

and X is a weakly coordinating anion;

and provided that;

when norbornene or substituted norbornene is present, no other monomer is present; and

when M is Pd a dene is not present.

453. The process as recited in claim 452 wherein 20 said temperature is about 20°C to about 100°C.

454. The process as recited in claim 452 wherein said olefin is ethylens or a linear α -olefin.

455. The process as recited in claim 452 wherein said olefin is ethylene.

 R^2 and R^5 are each independently hydrocarbyl, provided that the carbon atom bound to the imino nitrogen atom has at least two carbon atoms bound to it; and R^3 and R^4 are each independently hydrogen, hydrocarbyl, or R^3 and R^4 taken together are hydrocarbylene to form a ring.

457. The process as recited in claim 452 or 454 wherein a Lewis acid is also present.

458. The process as recited in claim 452 wherein M

35 is Ni(II).

459. The process as recited in claim 452 wherein M is PD(II)

5.

10

15

20

460. The process as recited in \not laim 452 wherein said π -allyl or π -benzyl group is selected from the group consisting of

$$CO_2R$$
 CO_2R

wherein R is hydrocarbyl.

461. A compound of the formula

$$\begin{array}{c|c}
R^3 & R^2 \\
N & A \\
N & X \\
XXXVII
\end{array}$$

wherein:

M is Ni(II) dr Pd(II);

A is a π -all ψ l or π -benzyl group;


 R^2 and R^5 are each independently hydrocarbyl or substituted hydrocarbyl, provided that the carbon atom bound directly to ψ he imino nitrogen atom has at least two carbon atoms bound to it;

R³ and R⁴ are each independently hydrogen, hydrocarbyl, substituted hydrocarbyl or R3 and R4 taken together are hydrocarbylene or substituted hydrocarbylene $t\phi$ form a ring;

each R^{17} is independently hydrocarbyl or substituted hydrocarbyl provided that any olefinic bond in said olefin as separated from any other olefinic

15

25



and X is a weakly coordinating anion; and provided that when M is Pd a diene is not present.

R² and R⁵ are each independently hydrocarbyl, provided that the carbon atom bound to the imino nitrogen atom has at least two carbon atoms bound to it; and R³ and R⁴ are each independently hydrogen, hydrocarbyl, or R³ and R⁴ taken together are hydrocarbylene to form a ring.

463. The compound as recited in claim 461 wherein M is Ni(II).

464. The compound as fecited in claim 461 wherein M is Pd(II).

465. The compound as recited in claim 461 wherein said π -allyl or π -benzyl group is selected from the group consisting of

$$\begin{array}{c} & & & & \\ & & \\ & & & \\ & & & \\ & & & \\ & & \\ & & & \\ & & & \\ & & & \\ & & & \\ & & & \\ & & & \\ &$$

wherein R is hydrocarbyl.

466. A compound of the formula

15

20

25

wherein:

R³ and R⁴ are each independently hydrogen, hydrocarbyl, substituted hydrocarbyl or R³ and R⁴ taken together are hydrocarbylene or substituted hydrocarbylene to form a ring;

 R^{54} is hydrocarbyl or substituted hydrocarbyl, provided that the carbon atom bound directly to the imino nitrogen atom has at least two carbon atoms bound to it;

each R⁵⁵ is independently hydrogen, hydrocarbyl, substituted hydrocarbyl, or a functional group;

W is alkylene or substituted alkylene containing 2 or more carbon atoms;

Z is a neutral Lewis base wherein the donating atom is nitrogen, sulfur, or oxygen, provided that if the donating atom is nitrogen then the pKa of the conjugate acid of that compound (measured in water) is less than about 6, or an olefin of the formula $R^{17}CH=CHR^{17}$;

each R¹⁷ is independently hydrogen, saturated hydrocarbyl or substituted saturated hydrocarbyl; and

X is a weakly coordinating anion; and provided that when M is Ni, W is alkylene and each R¹⁷ is independently hydrogen or saturated hydrocarbyl.

467. The compound as recited in claim 466 wherein R^3 and R^4 are each independently hydrogen or

10

15

20



hydrocarbyl, or R^3 and R^4 taken together are hydrocarbylene to form a ring; and R^{54} is hydrocarbyl.

468. The compound as recited in claim 466 or 467 wherein each R⁵⁵ is independently hydrogen or alkyl containing 1 to 10 carbon atoms.

469. The compound as recited in claim 466 wherein Z is neutral Lewis base.

470. The compound as redited in claim 469 wherein Z is a dialkyl ether.

Z is R¹⁷CH=CHR¹⁷.


472. The compound as recited in claim 471 wherein each R¹⁷ is independently hydrogen or alkyl.

473. The compound as recited in claim 471 wherein both of R^{17} are hydrogen.

474. The compound as recited in claim 466 wherein W is $-CH(CH_3)CH_2-$ or $-C/CH_3)_2CH_2-$.

475. The compound as recited in claim 471 wherein W is a divalent polymeric radical derived from the polymerization of $R^{17}CH=CHR^{17}$.

476. A process for the production of a compound of the formula




25 comprising, heating a compound of the formula

15

20

30



at a temperature of about -30°C to about +100° for a sufficient time to produce (XXXVIII), and wherein:

 R^3 and R^4 are each independently hydrogen, 5 hydrocarbyl substituted hydrocarbyl or R³ and R⁴ taken together are hydrocarbylene or substituted hydrocarbylene to form a ring;

R⁵⁴ is hydrocarbyl or substituted hydrocarbyl, provided that the carbon atom bound directly to the imino nitrogen atom has at least two carbon atoms bound to it;

each R^{45} is independently hydrogen, hydrocarbyl, substituted hydrocarbyl, or a functional group;

R⁵⁶ is alkyl containing 2 to 30 carbon atoms; T^5 is alk $\$ 1;

W is alky ene containing 2 to 30 carbon atoms; Z is a neutral Lewis base wherein the donating atom is nitrogen, sulfur, or oxygen, provided that if the donating atom is nitrogen then the pKa of the conjugate acid of that compound (measured in water) is less than about 6; and

X is a weakly coordinating anion.

477. The process as recited in claim 476 wherein R^3 and R^4 are each independently hydrogen or 25 hydrocarbyl, or R^3 and $\backslash R^4$ taken together are hydrocarbylene to form a ring; and R^{54} is hydrocarbyl.

478. The process as recited in claim 476 or 472 wherein each R⁵⁵ is independently hydrogen or alkyl containing 1 to 10 carbon atoms.

479. The process as recited in chaim 476 wherein Z is a dialkyl ether.

480. The process as recited in /claim 476 wherein W is $-CH(CH_3)CH_2-.or -C(CH_3)_2CH_2-$

481. The process as recited in claim 476, 477, 479 or 480 wherein T⁵ is methyl.

482. A process for the polymerization of olefins, comprising, contacting a compound of the formula

10

(XXXVIII) and one or more monomers selected from the group consisting of ethylene, an olefin of the formula R¹⁷CH=CH₂ or R¹⁷CH=CHR¹⁷, tyclobutene, cyclopentene, substituted norbornene, and norbornene,

wherein: 15

20

 R^3 and R^4 are ϕ ach independently hydrogen, hydrocarbyl, substituted hydrocarbyl or R3 and R4 taken together are hydrocarbylene or substituted hydrocarbylene to form a ring;

R⁵⁴ is hydrocarbyl or substituted hydrocarbyl, provided that the ϕ arbon atom bound directly to the imino nitrogen atom has at least two carbon atoms bound to it;

each R^{55} independently hydrogen,

hydrocarbyl, substituted hydrocarbyl, or a functional 25 group;

W is alkylene or substituted alkylene containing 2 of more carbon atoms;

Z is a neutral Lewis base wherein the donating atom is nitrogen, sulfur, or oxygen, provided that if 30 the donating atom is nitrogen then the pKa of the

10.

20

25

30

conjugate acid of that compound (measured in water) is less than about 6, or an olefin of the formula $R^{17}CH=CHR^{17}$;

each R17 is independently hydrogen, saturated hydrocarbyl or substituted saturated hydrocarbyl; and 5 X is a weakly coordinating anion;

and provided that:

when M is Ni, W is alkylene and each R17 is independently hydrogen or saturated hydrocarbyl;

and when norbornene or substituted norbornene is present, no other monomer is present.483. The process as recited in claim 482 wherein R3 and R4 are each independently hydrogen or hydrocarbyl, or R3 and R4 taken together are hydrocarbylene to form a ring; and R⁵⁴ is hydrocarbyl. 15

484. The process as recited in claim 482 or 483 wherein each R⁵⁵ is independently hydrogen or alkyl containing 1 to 10 carbon atoms.

485. The process as recited in claim 482 wherein Z is a dialkyl ether.

486. The process as recited in claim 482 wherein Z is R¹⁷CH=CHR¹⁷.

487. The process as recited in claim 482 wherein each R17 is independentl saturated hydrocarbyl or hydrogen.

488. The process as recited in claim 482 wherein both of R17 are hydrogen.

489. The process as recited in claim 482 wherein W is $-CH(CH_3)CH_2-OH_2-C(CH_3)_2CH_2-.$

490. The process as recited in claim 482 wherein said temperature is about 20°C to about 100°C.

491. The process as recited in claim 482 wherein said olefin is ethylene or a linear α -olefin.

492. The process as recited in claim 482 wherein said olefin is ethylene, propylene or a combination of 35 ethylene and propylene.

20



493. The process as recited in claim 486 wherein said olefin is ethylene, propylene or a combination of ethylene and propylene.

494. The process as recited in claim 489 wherein said olefin is cyclopentene.

495. The process as recited in claim 482 wherein said olefin is cyclopentene.

496. A homopolypropylene containing about 10 to about 700 Δ + methylene groups per 1000 methylene groups.

groups. 497. The homopolypropylene as recited in claim 496 containing about 25 to about 300 δ + methylene groups per 1000 methylene groups.

498. A homopolypropylene wherein a ratio of $\delta + : \gamma$ 15 methylene groups is about 0.5 to about 7.

499. The homopolypropylene as recited in claim 498 wherein said ratio is about 0.7 to 2.0.

500. A homopolypropylene in which about 30 to about 85 mole percent of monomer units are enchained in an ω ,1 fashion.

501. The homopolypropylene as recited in claim 500 wherein about 30 to about 60 mole percent of the monomer units are enchained in an ω ,1 fashion.

502. A process for the formation of linear α 25 olefins, comprising, contacting, at a temperature of about -100°C to about +200°C:

ethylene;

(VIII

and a Ni[I] of

 R^3 N R^4 N R^5

30

 $\mbox{\ensuremath{R^2}}$ and $\mbox{\ensuremath{R^5}}$ are each independently hydrocarbyl or substituted hydrocarbyl, provided that the carbon atom

20

25

30



bound to the imino nitrogen atom has at least two carbon atoms bound to it;

 R^3 and R^4 are each independently hydrogen, hydrocarbyl, substituted hydrocarbyl, or R3 and R4 taken together are hydrocarbylene or substituted hydrocarbylene to form a carbocyclic ring and

wherein an α -olefin containing 4 to 40 carbon atoms is produced.

503. The process as recited in claim 502 wherein said linear α -olefin has the formula $H_2C=CHR^1$, wherein 1Ó R^1 is n-alkyl containing 2 to 30 carbon atoms.

504. The process as recited in claim 502 wherein R^2 and R^5 are phenyl.

505. The process as recited in claim 502 wherein R^3 and R^4 are hydrogen, methyl or 1,8-naphthylylene.

506. The process as/recited in claim 503 wherein R³ and R⁴ are hydrogen, methyl or 1,8-naphthylylene.

507. The process as recited in claim 502 carried out at a temperature of about 25°C to about 100°C.

508. The process as recited in claim 502 wherein a partial pressure of said ethylene is about atmospheric pressure to about 275 MPa.

509. The process as recited in claim 502 wherein R^2 and R^5 are each independently hydrocarbyl, provided that the carbon atom bound to the imino nitrogen atom has at least two carbon atoms bound to it; and R3 and R4 are each independent hydrogen, hydrocarbyl, or R3 and R4 taken together are hydrocarbylene to form a ring.

510. A polymer blend comprising the polymer of claim 345, 349, 353, 354, 355, 358, 360 or 361 and one other polymer.

511. A nonwoven fabric wherein at least some fibers comprise the polymer of claim 345, 349, 353,

354, 355, 358, \$60 or 361. 35

512. A shaped part comprising the polymer of claim 345, 349, 353, 354, 355, 358, 360 or 361.

35



513. A sheet or film comprising the polymer of claim 345, 349, 353, 354, 355, 358, 360 or 361.

514. A nonwoven fabric or microfiber comprising the polymer of claim 345, 349, 353, 354, 355, 358, 360 or 361.

515. A laminate wherein one or more of the layers comprises the polymer of claim 345, 349, 353, 354, 355, 358, 360 or 361.

516. The laminate as recited in claim 511 wherein 10 a barrier layer is present.

517. A fiber comprising the polymer of claim 345, 349, 353, 354, 355, 358, 360 or 361.

518. A foam or foamed object comprising the polymer of claim 345, 349 353, 354, 355, 358, 360 or

361.
519. A microporous membrane comprising the polymer of claim 345, 349, 353, 354, 355, 358, 360 or 361.

520. The polymer of claim 345, 349, 353, 354, 355, 358, 360 or 361 which is crosslinked.

20 521. The polymer of claim 345, 349, 353, 354, or 355 which is heat treated.

522. The polymer as recited in claim 521 which has 20 percent or more crystallinity.

523. A composition comprising the polymer of claim 25 345, 349, 353, 354, 355, 358, 360 or 361 and a

nucleating agent.

524. A composition comprising the polymer of claim
345, 349, 353, 354, 355, 358, 360 or 361 and a flame
ratardant.

30 525. A composition comprising the polymer of claim 345, 349, 353, 354, 355, 358, 360 or 361 and an antioxidant.

526. A composition comprising the polymer of claim 345, 349, 353, 354, 355, 358, 360 or 361 and a filler

or reinforcer.

527. A composition comprising the polymer of claim
345, 349, 353 354, 355, 358, 360 or 361 which is
electrically conductive.

528 A process, comprising, contacting, at a temperature of about -80°C to about +20°C, a compound of the formula $(\eta^4-1,5-COD) PdMe_2$ and a diimine of the formula

5

a compound of the formula to produce

10

$$R^3$$
 N
 Me
 R^4
 R^5

(XXXXI)

wherein:

COD is 1,5 tyclooctadiene;

15

 R^2 and R^5 are each independently hydrocarbyl or substituted hydrocarbyl, provided that the carbon atom bound to the imino nitrogen atom has at least two carbon atoms bound to it; and


20

 R^3 and R^4 are each independently hydrogen, hydrocarbyl, substituted hydrocarbyl or R3 and R4 taken together are hydrocarbylene or substituted hydrocarbylene to form a ring.

529. The process as recited in claim 528 wherein said temperature is about -50°C to about +10°C.

25

530. The process as recited in claim 528 wherein R^2 and R^5 are both 2-t-butylphenyl or 2,5-di-tbutylphenyl, and R^3 and R^4 taken together are 1,8-



methyl 531. The process as recited in claim 528 wherein R^2 and R^3 are each independently hydrocarbyl, provided that the carbon atom bound to the imino nitrogen atom has at least two carbon atoms bound to it; and R^3 and R^4 are each independently hydrogen, hydrocarbyl, or R^3 and R^4 taken together are hydrocarbylene to form a

ring.

532. The compound as recited in claim 232, 248,

253, 259, 267, 317, 334, 339, 461 or 466 wherein X is

part of a heterogeneous support.

533. The compound as recited in claim 532 wherein said heterogeneous support is montmorillonite.

15 534. The process as recited in claim 49, 97, 176, 199, 280, 299, 451, 452 or 482 wherein X is part of a heterogeneous support.

535. The process as recited in claim 49, 97, 176, 199, 280, 299, 451, 452 or 482 wherein a polymerization catalyst is supported on a heterogeneous support.

536. The compound as recited in claim 232, 248, 253, 259, 267, 317, 334, 339, 461 or 466 which is supported on a heterogeneous support.

537. The prodess as recited in claim 49, 97, 176,

25 199, 280, 299, 451 452 or 482 wherein the polymerization is run in the gas phase.

538. The process as recited in claim 478 which is run in a fluidized bed reactor.

539. A flexible pouch made from a single or
30 multilayer film which comprises the polymer of claim 1,
3, 4, 6, 7, 332 or 343.

540. The polymer of claim 1, 3, 4, 6, 332 or 343 grafted with a compound containing ethylenic unsaturation and a functional group.

541. The polymer as recited in claim 540 wherein said functional group is carboxyl, carboxylic anhydride, ester or a carboxylate salt.

10.

20

25



542. A wrap packaging film having differential cling, comprising a film laminate having at least two layers;

an outer reverse layer which comprises a polymer of claim 1, 3, 4, 6, 7, 332 or 343, and a tackifier present in sufficent amount to impart cling properties; and

an outer obverse layer which has a density of at least about 0.916 g/mL and which has little or no cling; and

provided that a density of said outer reverse layer is at least 0.008 g/mL less than that of a density of said outer obverse layer.

543. A fine denier fiber comprising the polymer of claim 1, 3, 4, 6, 7, 332 or 343.

544. A composition, comprising, a polymer of claim 1, 3, 4, 6, 7, 332 or 343 and an antifogging agent.

545. The process as recited in claim 13, 15 or 142 wherein said bidentate ligand or second compound is (XXX) and n is 2, all of R^{30} , R^{28} and R^{29} are hydrogen, and both of R^{44} and R^{45} are 9-anthracenyl.

546. The process as recited in claim 65 or 84 wherein said compound or said second compound is (XVII) and n is 2, all of R^{30} , R^{28} and R^{29} are hydrogen, and both of R^{44} and R^{45} are 9 anthracenyl.

547. The process as recited in claim 65 or 84 wherein said compound or said second compound is (XVII) and n is 2, all of R^{30} , R^{28} and R^{29} are hydrogen, both of R^{44} and R^{45} are 9-anthracenyl, M is Ni, and n is 2.

548. The compound or process as recited in claim 299 or 317 wherein M is Ni or Pd and m is 2.

549. The process as recited in claim 299 wherein M is Ni.

550. The process as recited in claim 49 wherein said olefin comprises cyclopentene.

551. The process as recited in claim 65 wherein said olefin comprises cyclopentene.